

LAW OFFICES  
McGuireWoods LLP  
1750 TYSONS BOULEVARD, SUITE 1800  
MCLEAN, VIRGINIA 22102

APPLICATION  
FOR  
UNITED STATES  
LETTERS PATENT

Applicants: Kazuhiko Hayashi, Jinichi Fujikata,  
Tsutomu Ishi, Shigeru Mori, Keishi Ohashi,  
Masafumi Nakada, Kiyokazu Nagahara,  
Kunihiko Ishihara and Nobuyuki Ishiwata  
For: MAGNETO-RESISTANCE EFFECT  
ELEMENT, MAGNETO RESISTANCE  
EFFECT HEAD, MAGNETO-RESISTANCE  
TRANSDUCER SYSTEM, AND MAGNETIC  
STORAGE SYSTEM

Docket No.: 01FN046US

TITLE OF THE INVENTION

MAGNETO-RESISTANCE EFFECT ELEMENT, MAGNETO-RESISTANCE EFFECT HEAD,  
MAGNETO-RESISTANCE TRANSDUCER SYSTEM, AND MAGNETIC STORAGE SYSTEM

5 BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to a magneto-resistance  
effect element for writing and reading an information signal on  
magnetic storage media, a magneto-resistance effect head  
10 comprising the magneto-resistance effect element, a magneto-  
resistance transducer system comprising the magneto-resistance  
effect head, and a magnetic storage system comprising the  
magneto-resistance transducer system. More particularly, the  
present invention relates to a magneto-resistance effect element  
15 that reduces noise in a read signal.

Description of the Related Art

Conventionally disclosed is a magnetic read transducer  
that is referred to as a magneto-resistance sensor (hereinafter  
referred to as an MR sensor) or a head. This magnetic read  
20 transducer can read data from a magnetic surface at high linear  
densities. The MR sensor allows the read element to vary the  
electrical resistance as the function of the strength and the  
orientation of a magnetic flux applied from the outside in order  
to measure a variation in electrical resistance, thereby  
25 detecting a magnetic signal.

Such a conventional MR sensor operates based on the  
anisotropic magneto-resistance effect (hereinafter referred to as  
an AMR effect). By this effect, the component of a change in

electrical resistance of the read element varies in proportion to the second power of the cosine of the angle between the orientation of magnetization and the direction of the sense current flowing through the read element. The AMR effect is  
5 described in more detail in an article entitled "Memory, Storage, and Related Applications", D.A. Thompson, IEEE Transactions on Magnetism, Vol. MAG-11, No. 4, pp. 1039 (1975).

In addition, disclosed lately is a more prominent magneto-resistance effect by which a change in electrical resistance of  
10 the layered magnetic sensor is caused by spin-dependent transportation of conduction electrons between magnetic layers via a non-magnetic layer and spin-dependent scattering associated therewith at layer boundaries. This magneto-resistance effect is identified by various names such as the "giant magneto-resistance  
15 effect" or the "spin valve effect". Such a magneto-resistance sensor is formed of suitable materials to provide improved detection sensitivity and greater changes in electrical resistance in comparison with a sensor which makes use of the AMR effect. In a MR sensor of this type, in-plane resistance between  
20 a pair of ferromagnetic layers separated by a non-magnetic layer varies in proportion to the cosine of the angle between the orientations of magnetization of the aforementioned pair of ferromagnetic layers. In Japanese Patent Laid-Open Publication No. Hei 2-61572 submitted in July 1988, for claiming priority,  
25 described is a layered magnetic structure for providing a significant change in MR caused by an anti-parallel alignment of the orientations of magnetization in the magnetic layers.

On the other hand, such a phenomenon has been recently

discovered in which a relative change in orientation of magnetization of ferromagnetic bodies disposed above and below a very thin insulation layer (barrier layer) through which a tunneling current flows, causes a change in electrical resistance.

5 And, the layered structure made up of the ferromagnetic layer, the barrier layer, and the ferromagnetic layer is termed a ferromagnetic tunnel junction. For example, ferromagnetic tunnel junctions are introduced in "Journal of Applied Physics", Vol. 79 (8), No. 15, pp. 4724 (1996).

10 On the other hand, in a shield type element that makes use of a ferromagnetic tunnel junction, it is necessary to conduct a sense current for detecting a change in electrical resistance of the element in perpendicular relation to the tunnel junction. However, the structure similar to the shield type element  
15 employing the conventional spin valve presents a problem that the sense current flows through a vertical bias layer for controlling the magnetic domain of the free layer disposed near the tunnel junction to reduce the current flowing through the tunnel junction, thereby providing a reduced change in electrical  
20 resistance.

In order to overcome this problem, a read head was disclosed in Japanese Patent Laid-Open Publication No.Hei 10-162327 submitted on November 27, 1996, for claiming priority. The read head, employing a ferromagnetic tunnel junction film,  
25 has a structure in which the vertical bias layer is not in contact with the free layer.

Fig. 1 is a fragmentary sectional view illustrating the prior-art ferromagnetic tunnel head described in Japanese Patent

Laid-Open Publication No. Hei 10-162327. Fig. 1 illustrates the structure of a patterned ferromagnetic tunnel junction element, or a magneto-resistance effect element 30, having an insulation layer 11 disposed between a vertical bias layer 2b and a free layer 3b. This structure can prevent a sense current from flowing through the vertical bias layer 2b.

However, since the insulation layer 11 disposed between the vertical bias layer 2b and the free layer 3b acts also as a magnetic separation layer, it is difficult in the magneto-resistance effect element 30 to apply a vertical bias magnetic field of a sufficient magnitude to the free layer 3b. This presents such a problem that the magnetic domain of the free layer 3b is controlled insufficiently to cause the hysteresis of the R-H loop to increase for the shield type sensor, thereby providing a high-noise-level read signal upon reading magnetic information on a storage medium.

In order to overcome this problem, a read head was disclosed in Japanese Patent Laid-Open Publication No. Hei 10-255231 submitted on March 7, 1997, 1996, for claiming priority. The read head, employing a ferromagnetic tunnel junction film, has a structure in which the vertical bias layer is in contact with the free layer.

Figs. 2 and 3 are fragmentary sectional views of the ferromagnetic tunnel head described in Japanese Patent Laid-Open Publication No. Hei 10-255231. Figs. 2 and 3 illustrate the structure of a layered body comprising the free layer 3b, the non-magnetic layer 4, and the fixed layer 5, in which the vertical bias layer 2b is in direct contact with the end portion

of either the free layer 3b or the fixed layer 5.

However, the structure shown in Figs. 2 and 3 prevents the following problem. As will be described in the preferred embodiments of the present invention, the read head, which was actually fabricated to the structure shown in Figs. 2 and 3, caused the sense current to flow into the vertical bias layer 2b and thus insufficiently flow through the non-magnetic layer 4. It is thereby made impossible to provide sufficient output of the sense current. The low output made it impossible to provide sufficient (S/N) ratios and bit error rates. As described above, this structure may make it possible in principle to prevent the sense current from flowing through the vertical bias layer 2b and thereby bypassing the non-magnetic layer 4. However, the vertical bias layer 2b is disposed in close proximity to the end portion of the non-magnetic layer 4 in the layered body made up of the free layer 3b, the non-magnetic layer 4, and the fixed layer 5. Thus, it is difficult to fabricate this structure precisely enough to prevent the sense current from flowing through the vertical bias layer 2b and thereby bypassing the non-magnetic layer 4.

#### SUMMARY OF THE INVENTION

It is an object of the present invention to provide a magneto-resistance effect element, a magneto-resistance effect head, a magneto-resistance transducer system, and a magnetic storage system, which can prevent the sense current from flowing into the vertical bias layer, provide a read signal of a low noise level, and a good (S/N) ratio and bit error rate.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer and a free layer provided on the lower conductive layer and having an orientation of magnetization varied by a magnetic field applied thereto. The magneto-resistance effect element also comprises a non-magnetic layer provided on top of the free layer, a fixed layer provided on the non-magnetic layer and having a pinned orientation of magnetization, and a vertical bias layer, provided on the lower conductive layer, for applying a magnetic field to the free layer. The magneto-resistance effect element is adapted that the free layer is greater in length in the direction of a magnetic field applied thereto by the vertical bias layer than the fixed layer, and a sense current for detecting a change in electrical resistance of the non-magnetic layer flows substantially in perpendicular relation to the non-magnetic layer.

In the present invention, the free layer is made greater in length than the fixed layer in the direction of magnetic field applied by the vertical bias layer, thereby allowing only the free layer to be disposed near the vertical bias layer. This allows the vertical bias layer to effectively apply a vertical bias magnetic field to the free layer and makes it possible to prevent the leakage of a sense current from the fixed layer to the vertical bias layer. This allows almost all the sense current, which is applied to the magneto-resistance effect element to detect a change in electrical resistance, to flow through the non-magnetic layer, thereby making it possible to reduce noise in the read signal waveform and improve the (S/N) ratio and bit error rate. Incidentally, that the sense current

flows substantially in perpendicular relation to the  
aforementioned non-magnetic layer means that the sense current  
flows in orthogonal relation thereto to such an extent as to  
measure a change in electrical resistance of the non-magnetic  
5 layer without any trouble. In addition, the direction of the  
magnetic field applied by the aforementioned vertical bias layer  
agrees with the direction perpendicular to the direction in which  
the aforementioned sense current flows on a plane parallel to an  
air bearing surface of the magneto-resistance effect head.

10 In addition, it is preferable that the lower conductive  
layer has a recessed portion, and at least part of the vertical  
bias layer is buried in the recessed portion.

This makes it possible to place the vertical bias layer  
and the free layer to be flush with each other, and allows the  
15 vertical bias layer to apply a vertical bias magnetic field  
smoothly and effectively to the free layer.

Furthermore, at least part of the free layer can be  
brought into direct contact with the vertical bias layer.  
Alternatively, the underlying layer for free layer may be  
20 provided below the free layer such that the underlying layer for  
free layer is brought into contact with the vertical bias layer.  
A vertical bias layer protective layer may be provided on the  
vertical bias layer such that the vertical bias layer protective  
layer is brought into contact with the free layer or the  
25 underlying layer for free layer.

This allows the vertical bias layer to apply a vertical  
bias magnetic field more positively and effectively to the free  
layer.



A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a magnetic layer provided on the lower conductive layer, and a free layer provided on the magnetic layer and having an orientation of magnetization varied by a magnetic field coupled magnetically to the magnetic layer and applied thereto. The magneto-resistance effect element also comprises a non-magnetic layer provided on the free layer, a fixed layer provided on the non-magnetic layer and having a pinned orientation of magnetization, and a vertical bias layer, provided on the lower conductive layer, for applying a magnetic field to the free layer. The magneto-resistance effect element is adapted that the magnetic layer is greater in length in the direction of a magnetic field applied thereto by the vertical bias layer than the free layer, and a sense current for detecting a change in electrical resistance of the non-magnetic body flows substantially in perpendicular relation to the non-magnetic layer.

In addition, the magnetic layer can be magnetically coupled to the free layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, a second non-magnetic layer may be provided between the magnetic layer and the free layer.

In the present invention, a vertical bias magnetic field is once applied to the magnetic layer from the vertical bias layer, and then the vertical bias magnetic field is applied to the free layer from the magnetic layer. The vertical bias magnetic field is thus applied to the free layer through the two steps, thereby facilitating the control of the vertical bias magnetic field applied to the free layer. In addition, in the

direction of the magnetic field applied by the vertical bias layer, the free layer is made greater in length than the free layer, thereby placing only the magnetic layer near the vertical bias layer. This allows the vertical bias layer to effectively  
5 apply the vertical bias magnetic field to the magnetic layer and makes it possible to prevent the leakage of sense current from the layered body to the vertical bias layer, thereby allowing almost all sense current to conduct through the non-magnetic layer.

10 Furthermore, at least part of the magnetic layer can be brought into direct contact with the vertical bias layer. Alternatively, the underlying layer for magnetic layer may be provided below the magnetic layer such that the underlying layer for magnetic layer is brought into contact with the vertical bias  
15 layer. A vertical bias layer protective layer may be provided on the vertical bias layer such that the vertical bias layer protective layer is brought into contact with the magnetic layer or the underlying layer for magnetic layer.

This allows the vertical bias layer to apply a vertical  
20 bias magnetic field more positively and effectively to the magnetic layer.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a fixed layer provided on the lower conductive layer and having a pinned  
25 orientation of magnetization, and a non-magnetic layer provided on the fixed layer. The magneto-resistance effect element also comprises a free layer provided on the non-magnetic layer and having an orientation of magnetization varied by a magnetic field

applied thereto, a magnetic layer provided on the free layer and magnetically coupled to the free layer, and a vertical bias layer for applying a magnetic field to the magnetic layer. The magneto-resistance effect element is adapted that a sense current  
5 for detecting a change in electrical resistance of the non-magnetic layer flows substantially in perpendicular relation to the non-magnetic layer.

In addition, a fixing layer for pinning the orientation of magnetization of the fixed layer may be provided below the fixed  
10 layer.

Furthermore, it is preferable that at least part of the magnetic layer is brought into direct contact with the vertical bias layer. Alternatively, the underlying layer for magnetic layer may be provided below the magnetic layer such that the  
15 underlying layer for magnetic layer is brought into contact with the vertical bias layer. A vertical bias layer protective layer may be provided on the vertical bias layer such that the vertical bias layer protective layer is brought into contact with the magnetic layer or the underlying layer for magnetic layer.

20 In addition, the magnetic layer can be magnetically coupled to the free layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, the second non-magnetic layer may be provided between the magnetic layer and the free layer.

25 A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a fixed layer provided on the lower conductive layer and having a pinned orientation of magnetization, and a first non-magnetic layer

provided on the fixed layer. The magneto-resistance effect element also comprises a free layer provided on the first non-magnetic layer and having an orientation of magnetization varied by a magnetic field applied thereto. The magneto-resistance

5 effect element further comprises a first magnetic layer provided on the free layer and magnetically coupled to the free layer, a second magnetic layer provided on the first magnetic layer and magnetically coupled to the first magnetic layer, and a vertical bias layer for applying a magnetic field to the first and second  
10 magnetic layers. The magneto-resistance effect element is adapted that a sense current for detecting a change in electrical resistance of the first non-magnetic layer flows substantially in perpendicular relation to the first non-magnetic layer.

In addition, the first magnetic layer and the second  
15 magnetic layer are equal to or greater than the free layer in length in the direction of the magnetic field applied by the vertical bias layer, respectively.

Furthermore, a second non-magnetic layer can be provided between the free layer and the first magnetic layer, while a  
20 third non-magnetic layer can be provided between the first magnetic layer and the second magnetic layer. In addition, an underlying layer for fixing layer may be provided under the fixing layer.

In the present invention, a vertical bias magnetic field  
25 can be once applied to a three-layered film made up of the first magnetic layer, the third non-magnetic layer, and the second magnetic layer, from the vertical bias layer and then to the free layer from the three-layered film. As described above, the

vertical bias magnetic field is applied to the free layer from the vertical bias layer through two steps, thereby facilitating the control of the vertical bias magnetic field applied to the free layer.

5           Still furthermore, the product of saturation magnetization and film thickness of the first magnetic layer can be substantially equal to the product of saturation magnetization and film thickness of the second magnetic layer, and the three-layered film made up of the first magnetic layer, the third non-  
10           magnetic layer, and the second magnetic layer can be a layered antiferromagnetic body.

          This eliminates the sensitivity of the three-layered film to magnetic fields but provides only the free layer with the sensitivity to magnetic fields. For this reason, when the  
15           magneto-resistance effect element is incorporated into a read head, the read track width is determined only by the width of the free layer, thus making it possible to prevent the broadening of the effective track width. Incidentally, "being substantially  
20           equal" means "being equal to such an extent that an effect of reduction in sensitivity of the three-layered film to magnetic fields can be recognized".

          In addition, it is desirable that at least part of the first magnetic layer is in direct contact with the vertical bias layer. Alternatively, a first underlying layer for magnetic  
25           layer may be provided below the first magnetic layer such that the first underlying layer for magnetic layer is brought into contact with the vertical bias layer. A vertical bias layer protective layer may be provided on the vertical bias layer such

that the vertical bias layer protective layer is brought into contact with the first magnetic layer or the first underlying layer for magnetic layer. Similarly, it is desirable that at least part of the second magnetic layer is in direct contact with the vertical bias layer. Alternatively, a second underlying layer for magnetic layer may be provided below the second magnetic layer such that the second underlying layer for magnetic layer is brought into contact with the vertical bias layer. The vertical bias layer protective layer may also be brought into contact with the second magnetic layer or the second underlying layer for magnetic layer.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a fixed layer provided on the lower conductive layer and having a pinned orientation of magnetization, and a non-magnetic layer provided on the fixed layer. The magneto-resistance effect element also comprises a free layer provided on the non-magnetic layer and having an orientation of magnetization varied by a magnetic field applied thereto, a magnetic layer provided on the free layer, and a vertical bias layer, provided on the magnetic layer, for applying a magnetic field to the magnetic layer. The magneto-resistance effect element is adapted that a sense current for detecting a change in electrical resistance of the non-magnetic layer flows substantially in perpendicular relation to the non-magnetic layer.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a first fixed layer provided on the lower conductive layer and having a

pinned orientation of magnetization, and a first non-magnetic layer provided on the first fixed layer. The magneto-resistance effect element also comprises a first free layer provided on the first non-magnetic layer and having an orientation of magnetization varied by a magnetic field applied thereto. The magneto-resistance effect element further comprises a magnetic layer provided on the first free layer and magnetically coupled to the first free layer, and a second free layer provided on the magnetic layer and magnetically coupled to the magnetic layer.

10 The magneto-resistance effect element also comprises a second non-magnetic layer provided on the second free layer, a second fixed layer provided on the second non-magnetic layer and having a pinned orientation of magnetization, and a vertical bias layer for applying a magnetic field to the magnetic layer. The

15 magneto-resistance effect element is adapted that a sense current for detecting a change in electrical resistance of the first and second non-magnetic layers flows substantially in perpendicular relation to the first and second non-magnetic layers.

In addition, it is preferable that the magnetic layer is equal to or greater than the first and second free layers in length in the direction of the magnetic field applied by the vertical bias layer.

In the present invention, two pairs of free layers and fixed layers are provided to be vertically symmetric. This makes it possible to cancel out the effects of the magnetic field caused by sense current flowing through the free layers and the fixed layers, thereby providing a linear response to the magnetic field.

In addition, the first fixing layer for pinning the orientation of magnetization of the first fixed layer may be disposed below the first fixed layer, while the second fixing layer for pinning the orientation of magnetization of the second fixed layer may be disposed above the second fixed layer. Furthermore, the first underlying layer for fixing layer may be provided below the first fixing layer.

In addition, the first free layer can be magnetically coupled to the magnetic layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, the third non-magnetic layer may be provided between the first free layer and the magnetic layer. Likewise, the magnetic layer can be magnetically coupled to the second free layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, a fourth non-magnetic layer may be provided between the magnetic layer and the second free layer.

In addition, it is preferable that at least part of the magnetic layer is in direct contact with the vertical bias layer. Alternatively, the underlying layer for magnetic layer may be provided below the magnetic layer such that the underlying layer for magnetic layer is brought into contact with the vertical bias layer. A vertical bias layer protective layer may be provided on the vertical bias layer such that the vertical bias layer protective layer is brought into contact with the magnetic layer or the underlying layer for magnetic layer.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a first magnetic layer provided on the lower electrically conductive, and



a second magnetic layer provided on the first magnetic layer and magnetically coupled to the first magnetic layer. The magneto-resistance effect element also comprises a free layer provided on the second magnetic layer, magnetically coupled to the second  
5 magnetic layer, and having an orientation of magnetization varied by a magnetic field applied thereto. The magneto-resistance effect element further comprises a first non-magnetic layer provided on the free layer, a fixed layer provided on the first non-magnetic layer and having a pinned orientation of  
10 magnetization, and a vertical bias layer for applying a magnetic field to the first magnetic layer. The magneto-resistance effect element is adapted that a sense current for detecting a change in electrical resistance of the first non-magnetic layer flows substantially in perpendicular relation to the first non-magnetic  
15 layer.

In addition, it is preferable that the first magnetic layer is equal to or greater than the free layer in length in the direction of the magnetic field applied by the vertical bias layer. It is also preferable that the second magnetic layer is  
20 equal to or greater than the free layer in length in the direction of the magnetic field applied by the vertical bias layer.

Furthermore, a fixing layer for pinning the orientation of magnetization of the fixed layer may be disposed below the fixed  
25 layer.

Still furthermore, the first magnetic layer can be magnetically coupled to the second magnetic layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, a

second non-magnetic layer may be disposed between the first magnetic layer and the second magnetic layer. Likewise, the second magnetic layer can be magnetically coupled to the free layer by anti-ferromagnetic coupling or ferromagnetic coupling.

- 5 Furthermore, a third non-magnetic layer may be disposed between the second magnetic layer and the free layer.

Still furthermore, it is preferable that the product of saturation magnetization and film thickness of the first magnetic layer is substantially equal to the product of saturation  
10 magnetization and film thickness of the second magnetic layer. It is also preferable that a three-layered film made up of the first magnetic layer, the second non-magnetic layer, and the second magnetic layer is a layered antiferromagnetic body.

- Still furthermore, it is preferable that at least part of  
15 the first magnetic layer is in direct contact with the vertical bias layer. Alternatively, a first underlying layer for magnetic layer may be provided below the first magnetic layer such that the underlying layer for magnetic layer is brought into contact with the vertical bias layer. A vertical bias layer protective  
20 layer may be provided on the vertical bias layer such that the vertical bias layer protective layer is brought into contact with the magnetic layer or the underlying layer for magnetic layer. Likewise, it is preferable that at least part of the second magnetic layer is in direct contact with the vertical bias layer.  
25 Alternatively, an upper layer may be provided on the second magnetic layer such that the upper layer is brought into contact with the vertical bias layer. The vertical bias layer protective layer may be provided below the vertical bias layer such that the

vertical bias layer protective layer is brought into contact with the magnetic layer or the upper layer.

A magneto-resistance effect element according to the present invention comprises a lower conductive layer, a vertical  
5 bias layer provided on the lower conductive layer, a first magnetic layer provided on the vertical bias layer, and a second magnetic layer provided on the first magnetic layer and magnetically coupled to the first magnetic layer. The magneto-resistance effect element also comprises a free layer provided on  
10 the second magnetic layer, magnetically coupled to the second magnetic layer, and having an orientation of magnetization varied by a magnetic field applied thereto. The magneto-resistance effect element further comprises a first non-magnetic layer provided on the free layer, and a fixed layer provided on the  
15 first non-magnetic layer and having a pinned orientation of magnetization. The magneto-resistance effect element is adapted that a sense current for detecting a change in electrical resistance of the first non-magnetic layer flows substantially in perpendicular relation to the first non-magnetic layer.

20 In addition, it is preferable that the first magnetic layer is equal to or greater than the free layer in length in the direction of the magnetic field applied by the vertical bias layer. It is also preferable that the second magnetic layer is equal to or greater than the free layer in length in the  
25 direction of the magnetic field applied by the vertical bias layer. Furthermore, an underlying layer for vertical bias layer may be provided below the vertical bias layer.

Still furthermore, the first magnetic layer can be

magnetically coupled to the second magnetic layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, a second non-magnetic layer may be provided between the first magnetic layer and the second magnetic layer. Likewise, the  
5 second magnetic layer can be magnetically coupled to the free layer by anti-ferromagnetic coupling or ferromagnetic coupling. Furthermore, a third non-magnetic layer may be provided between the second magnetic layer and the free layer.

Still furthermore, it is preferable that the product of  
10 saturation magnetization and film thickness of the first magnetic layer is substantially equal to the product of saturation magnetization and film thickness of the second magnetic layer. It is preferable that a three-layered film made up of the first magnetic layer, the second non-magnetic layer, and the second  
15 magnetic layer is a layered antiferromagnetic body.

Still furthermore, it is preferable that at least part of the first magnetic layer is in direct contact with the vertical bias layer. Alternatively, an underlying layer for magnetic layer may be provided below the first magnetic layer such that  
20 the underlying layer for magnetic layer is brought into contact with the vertical bias layer. A vertical bias layer protective layer may be provided on the vertical bias layer such that the vertical bias layer protective layer is brought into contact with the magnetic layer or the underlying layer for magnetic layer.  
25 Similarly, it is desirable that at least part of the second magnetic layer is in direct contact with the vertical bias layer. Alternatively, an upper layer may be provided on the second magnetic layer such that the upper layer is brought into contact

with the vertical bias layer. An underlying layer for vertical bias layer may be provided below the vertical bias layer such that the underlying layer for vertical bias layer is brought into contact with the magnetic layer or the upper layer.

5           A magneto-resistance effect head according to the present invention comprises the magneto-resistance effect element and a lower shield layer serving as a substrate for the magneto-resistance effect element. The magneto-resistance effect head also comprises an upper conductive layer, provided on the  
10           magneto-resistance effect element, for inputting a sense current for detecting a change in electrical resistance of the magneto-resistance effect element into the magneto-resistance effect element; and an upper shield layer provided on the upper electrically conductive.

15           A magneto-resistance transducer system according to the present invention comprises the magneto-resistance effect head, an electric current generator circuit for supplying a sense current to the magneto-resistance effect head, and a data read circuit for detecting a change in electrical resistance of the  
20           magneto-resistance effect head to determine a magnetic field applied to the magneto-resistance effect head.

          A magnetic storage system according to the present invention comprises the magneto-resistance transducer system and a magnetic storage medium having a plurality of tracks for  
25           allowing the magneto-resistance transducer system to write and read data thereon. The magnetic storage system also comprises a first actuator for moving the magneto-resistance transducer system to where a selected track is located in the magnetic

storage medium, and a second actuator for rotatably driving the track.

The present invention makes it possible to provide a magneto-resistance effect head which has reduced noise in the read signal waveform and improved (S/N) ratio and bit error rate in comparison with the prior art. It is also possible to employ the magneto-resistance effect head to provide a high-performance magnetic read/write device and a magnetic memory device.

10 BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a prior-art;

15 Fig. 2 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a prior-art;

Fig. 3 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a prior-art;

20 Figs. 4 - 10 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a first embodiment of the present invention;

Fig. 11 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 12 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to another variation of this embodiment;

Figs. 13 - 21 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a second embodiment of the present invention;

5 Figs. 22 - 28 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a third embodiment of the present invention;

Figs. 29 - 31 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a fourth embodiment of the present invention;

10 Fig. 32 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

15 Fig. 33 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to another variation of this embodiment;

Figs. 34 - 37 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a fifth embodiment of the present invention;

20 Figs. 38 - 42 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a sixth embodiment of the present invention;

Figs. 43 - 49 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a seventh embodiment of the present invention;

25 Fig. 50 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 51 is a fragmentary sectional view illustrating the

structure of a magneto-resistance effect head according to another variation of this embodiment;

Fig. 52 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to still  
5 another variation of this embodiment;

Fig. 53 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to still another variation of this embodiment;

Fig. 54 is a fragmentary sectional view illustrating the  
10 structure of a magneto-resistance effect head according to still another variation of this embodiment;

Fig. 55 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to still another variation of this embodiment;

Fig. 56 is a fragmentary sectional view illustrating the  
15 structure of a magneto-resistance effect head according to still another variation of this embodiment;

Fig. 57 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to still  
20 another variation of this embodiment;

Figs. 58 - 64 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to an eighth embodiment of the present invention;

Fig. 65 is a fragmentary sectional view illustrating the  
25 structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 66 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to



another variation of this embodiment;

Figs. 67 - 70 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a ninth embodiment of the present invention;

5 Figs. 71 - 76 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a tenth embodiment of the present invention;

10 Fig. 77 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Figs. 78 - 87 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to an eleventh embodiment of the present invention;

15 Fig. 88 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 89 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to another variation of this embodiment;

20 Fig. 90 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to still another variation of this embodiment;

Figs. 91 - 94 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a twelfth embodiment of the present invention;

Fig. 95 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 96 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to another variation of this embodiment;

5 Figs. 97 - 102 are fragmentary sectional views illustrating a method for fabricating a magneto-resistance effect head according to a thirteenth embodiment of the present invention;

10 Fig. 103 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to a variation of this embodiment;

Fig. 104 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect head according to another variation of this embodiment;

15 Fig. 105 is a perspective view illustrating the structure of a magnetic read/write head according to a fourteenth embodiment of the present invention;

Fig. 106 is a schematic view illustrating the structure of a magneto-resistance transducer system according to this embodiment;

20 Fig. 107 is a block view illustrating the structure of a magnetic storage system according to this embodiment; and

Fig. 108 is a perspective view illustrating the structure of a magnetic storage system according to this embodiment.

25 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Now, the present invention will be explained below more specifically with reference to the accompanying drawings in accordance with the embodiments. Incidentally, all the

fragmentary sectional views employed in the embodiments of the present invention illustrate a magneto-resistance effect head cut in parallel to the surface of an air bearing. In addition, in the embodiments of the present invention, the expression of

5 "patterning" of layers or the like denotes allowing part of the layers or the like to remain and part thereof to be removed by etching or like means in illustrated regions within illustrated sections. Thus, this expression will never mean allowing part of the layers or the like to remain and part thereof to be removed

10 by etching or like means in non-illustrated sections or regions. In other words, in the embodiments of the present invention, the layers or the like that are not denoted with the expression of "patterning" may also allow part thereof to remain and part thereof to be removed by etching or like means in non-illustrated

15 sections or regions.

Now, described below are a magneto-resistance effect head according to a first embodiment of the present invention and a method for fabricating the head. Figs. 4 - 10 are fragmentary sectional views illustrating the steps of the method for

20 fabricating the magneto-resistance effect head according to this embodiment in the order in which they appear in the method.

First, as shown in Fig. 4, a lower shield layer 16 and a lower conductive layer 1 are formed successively on a substrate (not shown).

25 Then, as shown in Fig. 5, a photoresist 20 having an opening portion 20a is formed on the lower conductive layer 1, which is in turn etched by dry etching or like means to form a recessed portion 1a on the surface of lower conductive layer 1.

Then, as shown in Fig. 6, on the recessed portion 1a of the lower conductive layer 1, deposited are an underlying layer for vertical bias layer 2a and a vertical bias layer 2b so as to be partially buried in the recessed portion of the lower  
5 conductive layer 1, and thereafter the photoresist 20 is removed.

Then, as shown in Fig. 7, on the lower conductive layer 1 and the vertical bias layer 2b, formed and stacked in the following order are an underlying layer for free layer 3a, a the free layer 3b, a non-magnetic layer 4, a fixed layer 5, a fixing  
10 layer 6b, and an upper layer 7.

Then, as shown in Fig. 8, there is formed a photoresist 21 immediately below the upper surface of the upper layer 7 so as to cover the central portion of the region where the vertical bias layer 2b is not formed. Then, with the photoresist 21 being  
15 employed as a mask, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are etched by dry etching or the like to form an insulation layer 11 so as to be buried in the etched portion. At this time, the upper surface of the upper layer 7 is exposed on the upper surface of the  
20 insulation layer 11.

Then, as shown in Fig. 9, the photoresist 21 is removed. Then, a magneto-resistance effect element 31a is formed which is made up of the lower conductive layer 1, the underlying layer for vertical bias layer 2a, the vertical bias layer 2b, the  
25 underlying layer for free layer 3a, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer.

Then, as shown in Fig. 10, there is deposited an upper

conductive layer 15 on the upper layer 7 and the insulation layer 11, and a photoresist (not shown) is formed, which is in turn employed as a mask to pattern the upper conductive layer 15 by dry etching or the like. Thereafter, the photoresist is removed  
5 on which formed is an upper shield layer 17, thereby forming a magneto-resistance effect head 61a.

Now, the structure of the magneto-resistance effect head 61a according to this embodiment is described. As shown in Fig. 10, provided are the lower shield layer 16 and the lower  
10 conductive layer 1. The lower conductive layer 1 has the recessed portion 1a, and the recessed portion 1a is provided with the underlying layer for vertical bias layer 2a and the vertical bias layer 2b. The underlying layer for free layer 3a and the free layer 3b are provided in the portion of the lower conductive  
15 layer 1, where provided is neither the underlying layer for vertical bias layer 2a nor the vertical bias layer 2b, and on the vertical bias layer 2b. On top of the free layer 3b, formed in the following order are the non-magnetic layer 4 patterned so as not to be disposed immediately above the vertical bias layer 2b,  
20 the fixed layer 5, the fixing layer 6b, and the upper layer 7.

In addition, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are buried in the insulation layer 11, and the upper surface of the upper layer 7 is exposed to the upper surface of the insulation layer 11.  
25 Furthermore, on top of the upper layer 7 and the insulation layer 11, provided is the upper conductive layer 15, on top of which the upper shield layer 17 is formed.

In the aforementioned structure, the lower conductive

layer 1 and the upper conductive layer 15 act as the upper and lower electrodes for conducting a sense current in the direction perpendicular to stacked layer planes. Here, the stacked layer planes are formed of the underlying layer for free layer 3a  
5 disposed between the lower conductive layer 1 and the upper conductive layer 15, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7. Materials forming the lower conductive layer 1 and the upper conductive layer 15 include a single material of one type, a  
10 mixture of materials of two or more types, a compound of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Au, Ag, Cu, Mo, W, Y, Ti, Zr, Hf, V, Nb, Pt, and Ta. In particular, Au, Ag, Cu, Pt, and Ta are more favorable. In  
15 addition, materials forming the substrate include an altic, SiC, and alumina.

In addition, the vertical bias layer 2b is to apply a vertical bias magnetic field to the free layer 3b, while the underlying layer for vertical bias layer 2a is to improve the  
20 film quality such as the crystallization property of the vertical bias layer 2b and the magnetic properties of the vertical bias layer 2b. Materials forming the underlying layer for vertical bias layer 2a include a single material of one type, a mixture of materials of two or more types, or a multi-layered film formed of  
25 materials of two or more types, which are selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, V, Fe, FeCo, FeCoNi, and NiFe. In particular, Cr, Fe, and CoFe are more favorable. On the other

hand, materials forming the vertical bias layer 2b include a single material of one type, a mixture of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of

5 CoCrPt, CoCr, CoPt, CoCrTa, FeMn, NiMn, Ni oxide, NiCo oxide, Fe oxide, NiFe oxide, IrMn, PtMn, PtPdMn, ReMn, Co ferrite, and Ba ferrite. In particular, CoCrPt, CoCrTa, CoPt, NiMn, and IrMn are more favorable.

When an external magnetic field is applied to a magnetic  
10 sensor including the magneto-resistance effect head 61a, the free layer 3b acting as a magnetic layer changes the orientation of magnetization in accordance with the direction and the magnitude of the magnetic field. An external magnetic field is applied to the free layer 3b via the vertical bias layer 2b. In addition,  
15 the underlying layer for free layer 3a is to improve the film quality such as the crystallization property of the free layer 3b and the magnetic properties of the free layer 3b. Materials forming the underlying layer for free layer 3a include a single material of one type, a mixture of materials of two or more types,  
20 a compound of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V. In particular, Ta, Zr, and Hf are more favorable. Materials forming  
25 the free layer 3b include alloys and amorphous magnetic materials such as NiFe, CoFe, NiFeCo, FeCo, CoFeB, CoZrMo, CoZrNb, CoZr, CoZrTa, CoHf, CoTa, CoTaHf, CoNbHf, CoZrNb, CoHfPd, CoTaZrNb, and CoZrMoNi. As an additive element, one or more types of elements

selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V can also be employed. More favorable are NiFe, a two-layer film of NiFe/CoFe, a two-layer film of NiFe/NiFeCo, and a two-layer film  
5 of NiFe/Co.

The fixing layer 6b is to pin the orientation of magnetization of the fixed layer 5, while the underlying layer for fixing layer 6a is to improve the film quality such as the crystallization property of the fixing layer 6b and the magnetic  
10 properties of the fixing layer 6b. On the other hand, the fixed layer 5 has an orientation of magnetization that is pinned by the fixing layer 6b.

Materials forming the underlying layer for fixing layer 6a include a single material of one type, a mixture of materials of  
15 two or more types, a compound of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V. In particular, Ta, Zr, and Hf are more favorable. On the  
20 other hand, as a material for the fixing layer 6b, it is possible to employ FeMn, NiMn, IrMn, RhMn, PtPdMn, ReMn, PtMn, PtCrMn, CrMn, CrAl, TbCo, CoCr, CoCrPt, CoCrTa, PtCo and the like. In particular, a favorable material is PtMn or PtMn to which doped is at least one type of element selected from the group  
25 consisting of Ti, V, Cr, Co, Cu, Zn, Y, Zr, Nb, Mo, Tc, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt, Au, Si, and Al.

As materials forming the fixed layer 5, it is possible to use alloys and amorphous magnetic materials such as NiFe, Co,



In addition, it is also possible to use a layered film of those materials combined with at least one type of metal or an alloy of the metals selected from the group consisting of Ti, V, Cr, Cu, Zn, Y, Zr, Nb, Mo, Tc, Ra, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt, Au, Si, Al, and Ni. In particular, three-layer films such as Co/Ru/Co, CoFe/Ru/CoFe, CoFeNi/Ru/CoFeNi, Co/Cr/Co, CoFe/Cr/CoFe, and CoFeNi/Cr/CoFeNi are favorable.

10                    Then, <sup>non-</sup>~~on-~~ magnetic layer 4 is disposed between the free  
                         ^  
layer 3b and the fixed layer 5, varying in electrical resistance  
in accordance with the angle between the orientation of  
magnetization of the free layer 3b and that of the fixed layer 5.  
As materials forming the non-magnetic layer 4, used are metal,  
15 oxide, nitride, a mixture of oxide and nitride, a multi-layered  
film of metal and oxide, a multi-layered film of metal and  
nitride, or a multi-layered film a mixture of metal, oxide, and  
nitride. And, the metals include at least one type of metal  
selected from the group consisting of Ti, V, Cr, Co, Cu, Zn, Y,  
20 Zr, Nb, Mo, Tc, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt, Au, Si,  
Al, Ti, Ta, Pt, Ni, Co, Re, and V. The oxides are formed of  
these metals and the nitrides are also formed of these metals.  
In particular, Al oxide and Cu are favorable.

In addition, the upper layer 7 is to prevent the layer disposed thereunder from being corroded during the processes for fabricating the magneto-resistance effect head 61a and in the service environment. Materials forming the upper layer 7 include a single material of one type, a mixture of materials of two or

more types, a compound of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Au, Ag, Cu, Mo, W, Y, Ti, Pt, Zr, Hf, V, Nb, Ta, and Ru. In particular, Ta, Zr, and  
5 Ti are favorable.

Furthermore, the insulation layer 11 is to prevent the leakage of a sense current flowing through the non-magnetic layer 4. Materials forming the insulation layer 11 include a single material, a mixture of materials, and a multi-layered film formed  
10 of materials, which are selected from the group consisting of Al oxide, Si oxide, aluminum nitride, silicon nitride, and diamond-like carbon.

Still furthermore, materials forming the lower shield layer 16 and the upper shield layer 17 include a single material  
15 of one type, a mixture of materials of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of NiFe, CoZr, CoFeB, CoZrMo, CoZrNb, CoZrTa, CoHf, CoTa, CoTaHf, CoNbHf, CoZrNb, CoHfPd, CoTaZrNb, CoZrMoNi, FeAlSi, a Fe nitride base material,  
20 MnZn ferrite, NiZn ferrite, and MgZn ferrite.

Now, the operation of the magneto-resistance effect head 61a is explained below. When an external magnetic field is applied to the magneto-resistance effect head 61a, a magnetic field is applied to the free layer 3b via the vertical bias layer  
25 2b, causing the orientation of magnetization of the free layer 3b to change in accordance with the direction and magnitude of the magnetic field applied thereto. And, since the orientation of magnetization of the fixed layer 5 is pinned by the fixing layer

6b, a change occurs in orientation of magnetization between the fixed layer 5 and the free layer 3b, causing a change in electrical resistance of the non-magnetic layer 4. In this state, the lower conductive layer 1 and the upper conductive layer 15 allow a sense current to flow in the direction perpendicular to the non-magnetic layer 4 to measure the electrical resistance of the non-magnetic layer 4, thereby making it possible to detect the external magnetic field.

Now, an effect of this embodiment is described. As shown in Fig. 10, the magneto-resistance effect head 61a according to this embodiment has the free layer 3b which is greater than the fixed layer 5 in length, and only the free layer 3b is disposed near the vertical bias layer 2b. This allows the vertical bias layer 2b to apply a magnetic field positively and effectively to the free layer 3b and makes it possible to prevent the leakage of a sense current from the fixed layer 5 to the vertical bias layer 2b. This allows almost all the sense current applied to flow through the non-magnetic layer 4, thereby improving the performance of the magneto-resistance effect head 61a.

Furthermore, part of the direction of thickness of the patterned underlying layer for vertical bias layer 2a and the vertical bias layer 2b is buried in the recessed portion 1a of the lower conductive layer 1. This provides a gradual slope to the end portion of the underlying layer for vertical bias layer 2a and the vertical bias layer 2b, thereby allowing the vertical bias layer 2b to apply a vertical bias magnetic field to the free layer 3b more effectively.

Figs. 11 and 12 are fragmentary sectional views

illustrating a variation of the magneto-resistance effect element according to this embodiment. Fig. 11 illustrates a magneto-resistance effect element 31b having the free layer 3b patterned to bring the end portion thereof into contact with that of the vertical bias layer 2b.

On the other hand, Fig. 12 illustrates a magneto-resistance effect element 31c having the free layer 3b patterned to make the end portion thereof overlap that of the vertical bias layer 2b. Like the magneto-resistance effect element 31a, the magneto-resistance effect element 31c shown in Figs. 11, 12 can constitute the magneto-resistance effect head.

Incidentally, this embodiment has shown that the non-magnetic layer 4 patterned in conjunction with the fixed layer 5, the fixing layer 6b, and the upper layer 7. However, the non-magnetic layer 4 can be extended like the free layer 3b. Alternatively, the non-magnetic layer 4 may be patterned to be larger than the fixing layer 6b and the fixing layer 6b and smaller than the free layer 3b.

In addition, the underlying layer for vertical bias layer 2a, the underlying layer for free layer 3a, and the upper layer 7 may be omitted, and a protective layer for protecting the vertical bias layer may be provided on top of the vertical bias layer 2b.

Furthermore, this embodiment has shown that the lower shield layer 16 and the lower conductive layer 1 provided separately. However, the lower shield layer 16 and lower conductive layer 1 may be a common layer. In this case, the lower conductive layer 1 is omitted. In addition, the upper

conductive layer 15 and the upper shield 17 may be a common layer. In this case, the upper conductive layer 15 is omitted. This allows the gap between the top and bottom shield layers to be made smaller. Furthermore, an upper gap layer may be provided  
5 between the upper conductive layer 15 and the shield layer 17 or a lower gap layer may be provided between the lower shield layer 16 and the lower conductive layer 1.

Now, a second embodiment of the present invention is described below. Figs. 13 - 21 are fragmentary sectional views  
10 illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

First, as shown in Fig. 13, the lower shield layer 16 and the lower conductive layer 1 are successively formed on a  
15 substrate (not shown).

Then, as shown in Fig. 14, the photoresist 20 having the opening portion 20a is formed on top of the lower conductive layer 1 which is etched by dry etching or like means to form the recessed portion 1a on the surface of the lower conductive layer  
20 1.

Then, as shown in Fig. 15, the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are deposited on top of the lower conductive layer 1 after the photoresist 20 has been removed.

25 Then, as shown in Fig. 16, the photoresist 21 is formed to cover the region having the recessed portion 1a arranged immediately below the vertical bias layer 2b and provide an opening portion 21a for the region having no recessed portion 1a

arranged immediately below the vertical bias layer 2b.

Subsequently, with the photoresist 21 being employed as a mask,  
the underlying layer for vertical bias layer 2a and the vertical  
bias layer 2b are etched and thereby patterned by dry etching or  
5 like means.

Then, as shown in Fig. 17, on top of the lower conductive  
layer 1 and vertical bias layer 2b, formed and layered in the  
following order are the underlying layer for free layer 3a, the  
free layer 3b, the non-magnetic layer 4, the fixed layer 5, the  
10 fixing layer 6b, and the upper layer 7.

Then, as shown in Fig. 18, a photoresist 22 is provided to  
cover the region having no vertical bias layer 2b arranged  
immediately below the upper layer 7. With the photoresist 22  
being employed as a mask, the underlying layer for free layer 3a,  
15 the free layer 3b, the non-magnetic layer 4, the fixed layer 5,  
the fixing layer 6b, and the upper layer 7 are patterned by dry  
etching or like means.

Then, as shown in Fig. 19, the photoresist 22 is removed  
to form a photoresist 23 on top of the upper layer 7 to cover the  
20 central portion of the upper layer 7. With the photoresist 23  
being employed as a mask, the non-magnetic layer 4, the fixed  
layer 5, the fixing layer 6b, and the upper layer 7 are patterned  
by dry etching or like means.

Then, as shown in Fig. 20, the periphery of the pattern of  
25 the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b,  
and the upper layer 7 is buried in the insulation layer 11,  
thereby forming a magneto-resistance effect element 32a. Then,  
as shown in Fig. 21, after the photoresist 23 has been removed,

the upper conductive layer 15 is deposited on top of the upper layer 7 and the insulation layer 11 and then a photoresist (not shown) is formed. With this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Then, this photoresist is removed to form the upper shield layer 17 thereon and thus a magneto-resistance effect head 62a is formed.

Now, the structure of the magneto-resistance effect head 62a according to this embodiment is described below. As shown in Fig. 21, the magneto-resistance effect head 62a according to this embodiment has a different shape of the underlying layer for free layer 3a and the free layer 3b in comparison with the magneto-resistance effect head 61a according to the first embodiment shown in Fig. 10. In this embodiment, the end portion of the underlying layer for free layer 3a and the free layer 3b is flush and in contact with that of the underlying layer for vertical bias layer 2a and the vertical bias layer 2b. In the magneto-resistance effect head 62a according to this embodiment, the structure and operation thereof is the same as those of the magneto-resistance effect head 61a according to the aforementioned first embodiment except for the shape of the underlying layer for free layer 3a and the free layer 3b.

Incidentally, in this embodiment, it has been explained in which the non-magnetic layer 4 is patterned in conjunction with the fixed layer 5, the fixing layer 6b, and the upper layer 7. However, like the first embodiment, the non-magnetic layer 4 may be extended as the free layer 3b. Alternatively, the non-magnetic layer 4 may be patterned to be larger than the pattern

of the fixed layer 5, the fixing layer 6b, and the upper layer 7, and smaller than the pattern of the free layer 3b.

Furthermore, in this embodiment, it has been explained in which the upper conductive layer 15 is patterned, however, the upper conductive layer 15 may be extended without being patterned.

Now, described below is a third embodiment according to the present invention. Figs. 22 - 28 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

First, as shown in Fig. 22, the lower shield layer 16 and the lower conductive layer 1 are successively formed on a substrate (not shown).

Then, as shown in Fig. 23, the photoresist 20 having the opening portion 20a is formed on top of the lower conductive layer 1, which is then etched by dry etching or like means to form the recessed portion 1a on the surface of the lower conductive layer 1.

Then, as shown in Fig. 24, with the photoresist 20 being employed as a mask, the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are deposited so as to partially fill in the recessed portion 1a of the lower conductive layer 1, and then the photoresist 20 is removed.

Then, as shown in Fig. 25, on top of the lower conductive layer 1 and the vertical bias layer 2b, formed and layered in the following order are the underlying layer for free layer 3a, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.



Then, as shown in Fig. 26, the photoresist 21 is provided to cover the central portion of the region having no vertical bias layer 2b arranged immediately below the upper surface of the upper layer 7. With the photoresist 21 being employed as a mask, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are patterned by dry etching or like means. Then, the periphery of the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 is buried in the insulation layer 11.

Then, as shown in Fig. 27, the photoresist 21 is removed to form the photoresist 22, patterned to cover a region broader than that covered by the photoresist 21, at a position on the upper layer 7 and the insulation layer 11 where the photoresist 21 has once been formed. With the photoresist 22 being employed as a mask, the underlying layer for free layer 3a, the free layer 3b, and the insulation layer 11 are etched by dry etching or like means and thereby patterned. Subsequently, this etched region is buried in the insulation layer 11b to thereby form a magneto-resistance effect element 32b.

Then, as shown in Fig. 28, the photoresist 22 is removed. Thereafter, the upper conductive layer 15 is deposited on top of the upper layer 7, the insulation layer 11, and the insulation layer 11b to form a photoresist (not shown), which is in turn employed to pattern the upper conductive layer 15 by dry etching or like means. Then, this photoresist is removed and the upper shield layer 17 is formed thereupon to form a magneto-resistance effect head 62b.

The magneto-resistance effect head 62b formed according to

this embodiment has the same structure and operation as those of the magneto-resistance effect head 62a according to the second embodiment except that the insulation layers 11 and 11b are formed through two steps.

5           Now, a magneto-resistance effect head according to a fourth embodiment of the present invention and the method for fabricating the head are described below. Figs. 29 - 34 are fragmentary sectional views illustrating the steps of the method for fabricating the magneto-resistance effect head according to  
10 this embodiment in the order in which they appear.

First, by the steps shown in Figs. 4 - 6 in the first embodiment, a layered body as shown in Fig. 6 is formed.

Then, as shown in Fig. 29, on top of the lower conductive layer 1 and the vertical bias layer 2b, the following layers are  
15 formed and layered. That is, an underlying layer for magnetic layer 8a, a magnetic layer 8b, a second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are formed and layered in that order.

20           Then, as shown in Fig. 30, the photoresist 21 is formed so as to partially cover the region having no vertical bias layer 2b arranged immediately below the upper surface of the upper layer 7. Then, the second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer  
25 6b, and the upper layer 7 are etched by dry etching or the like. Then, the insulation layer 11 is formed to bury the etched portion therein, thus forming a magneto-resistance effect element 33a on top of the lower shield layer 16.

Then, as shown in Fig. 31, the photoresist 21 is removed and the upper conductive layer 15 is deposited on the upper layer 7 and the insulation layer 11. Then, a photoresist (not shown) is formed to pattern the upper conductive layer 15 by dry etching or the like and thereafter the photoresist is removed, on which the upper shield layer 17 is formed, thereby forming a magneto-resistance effect head 63a.

Now, the structure of the magneto-resistance effect head 63a according to this embodiment is described below. As shown in Fig. 31, the magneto-resistance effect head 63a is characterized in that the magnetic layer 8b is provided below the free layer 3b via the non-magnetic layer 9.

As shown in Fig. 31, the lower shield layer 16 and the lower conductive layer 1 are provided on the substrate (not shown), the lower conductive layer 1 has the recessed portion 1a, and the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are provided on the recessed portion 1a. On top of the portion having no underlying layer for vertical bias layer 2a and no vertical bias layer 2b on the lower conductive layer 1 and on top of the vertical bias layer 2b, provided are the underlying layer for magnetic layer 8a and the magnetic layer 8b. On top of the magnetic layer 8b, layered in the following order are the second non-magnetic layer 9 that is not patterned immediately above the vertical bias layer 2b, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.

In addition, the second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the

fixing layer 6b, and the upper layer 7 are buried in the insulation layer 11, the upper surface of upper layer 7 is exposed to the upper surface of the insulation layer 11.

Furthermore, the upper conductive layer 15 is patterned on the upper layer 7 and the insulation layer 11, and the upper shield layer 17 is provided on the upper conductive layer 15.

In the aforementioned structure, the magnetic layer 8b is to transmit a vertical bias magnetic field applied by the vertical bias layer 2b to the free layer 3b by means of magnetic coupling such as ferromagnetic coupling, antiferromagnetic coupling, or magneto-static coupling. In addition, the second non-magnetic layer 9 allows the component material and the film thickness thereof to control the magnetic coupling between the magnetic layer 8b and the free layer 3b. The underlying layer for magnetic layer 8a is to improve film quality such as the crystallization properties of the magnetic layer 8b and provide good magnetic properties for the magnetic layer 8b. Incidentally, the non-magnetic layer 4 is an insulation layer for conducting a tunneling current therethrough, whereas the second non-magnetic layer 9 is an electrically conductive layer for controlling the magnetic coupling between the magnetic layer 8b and the free layer 3b.

As materials forming the magnetic layer 8b, employed are alloys such as NiFe, Co, CoFe, NiFeCo, FeCo, CoFeB, CoZrMo, CoZrNb, CoZr, CoZrTa, CoHf, CoTa, CoTaHf, CoNbHf, CoZrNb, CoHfPd, CoTaZrNb, and CoZrMoNi, a single-layer film of an amorphous magnetic material, a mixture film, or a multi-layered film. In particular, NiFe, Co, CoFe, NiFeCo, or FeCo is favorable. On the

other hand, as an additive element, it is possible to use one or more types of elements selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V.

5           Materials forming the second non-magnetic layer 9 include a single material of one type, a mixture of materials of two or more types, a compound of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Ti, V, Cr, Co, Cu, Zn, Y, Zr, Nb, Mo, 10   Tc, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt, Au, Si, Al, Ti, Ta, Pt, Ni, Co, Re, and V. In particular, Ru and Cr are favorable. Materials forming the underlying layer for magnetic layer 8a include a single material of one type, a mixture of materials of two or more types, a compound of two or more types, or a multi- 15   layered film formed of materials of two or more types, which are selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V. In particular, Ta and Zr are more favorable.

          The component material and the function of other layers of 20   the magneto-resistance effect head 63a according to this embodiment are the same as those of each of the layers of the magneto-resistance effect head 61a according to the aforementioned first embodiment.

          Now, described below is the operation of the magneto- 25   resistance effect head 63a. Application of an external magnetic field to the magneto-resistance effect head 63a will cause a magnetic field to be applied to the magnetic layer 8b via the vertical bias layer 2b. Then, a vertical bias magnetic field is

applied by the magnetic layer 8b via the second non-magnetic layer 9 to the free layer 3b by means of magnetic coupling such as ferromagnetic coupling, antiferromagnetic coupling, or magneto-static coupling. And, the orientation of magnetization  
5 of the free layer 3b changes in accordance with the direction and the magnitude of this magnetic field. Since the orientation of magnetization of the fixed layer 5 is pinned by the fixing layer 6b, a change occurs in orientation of magnetization between the fixed layer 5 and the free layer 3b, causing a change in  
10 electrical resistance of the non-magnetic layer 4. In this state, the lower conductive layer 1 and the upper conductive layer 15 allow a sense current to flow in the direction perpendicular to the non-magnetic layer 4 to measure the electrical resistance of the non-magnetic layer 4, thereby making it possible to detect  
15 the external magnetic field.

Now, an effect of this embodiment is described below. In the magneto-resistance effect head 63a according to this embodiment, a vertical bias magnetic field is applied to the free layer 3b from the vertical bias layer 2b through two steps of  
20 process, thereby assuring the application of the vertical bias magnetic field and facilitating the control of the amount of application of the magnetic field. In addition, as shown in Fig. 31, the free layer 3b and the fixed layer 5 are not arranged near the vertical bias layer 2b but only the magnetic layer 8b is  
25 disposed near the vertical bias layer 2b. This allows the vertical bias layer 2b to apply a magnetic field to the magnetic layer 8b positively and effectively, also making it possible to prevent the leakage of sense current from the free layer 3b or

the fixed layer 5 to the vertical bias layer 2b.

Figs. 32 and Fig. 33 are fragmentary sectional views illustrating a variation of the magneto-resistance effect element according to this embodiment. Fig. 32 illustrates a magneto-resistance effect element 33b in which the magnetic layer 8b is patterned so that the end portion of the magnetic layer 8b is in contact with that of the vertical bias layer 2b.

In addition, Fig. 33 illustrates a magneto-resistance effect element 33b in which the magnetic layer 8b is patterned so that the end portion of the magnetic layer 8b overlaps the vertical bias layer 2b. The magneto-resistance effect elements 33b, 33c, shown in Figs. 32 and 33, can constitute the magneto-resistance effect head.

Incidentally, in this embodiment, it has been explained in which the second non-magnetic layer 9, the free layer 3b, and the non-magnetic layer 4 are patterned in conjunction with the fixed layer 5, the fixing layer 6b, and the upper layer 7. However, the second non-magnetic layer 9, the free layer 3b, and the non-magnetic layer 4 may be extended as the magnetic layer 8b or may be patterned to be larger than the pattern of the fixed layer 5, the fixing layer 6b, and the upper layer 7 and smaller than the pattern of the magnetic layer 8b. Furthermore, the pattern of the second non-magnetic layer 9 may be extended further than that of the free layer 3b or the pattern of the free layer 3b may be extended further than that of the non-magnetic layer 4.

In addition, the underlying layer for vertical bias layer 2a, the underlying layer for magnetic layer 8a, the second non-magnetic layer 9, and the upper layer 7 may be omitted, and a

protective layer for protecting the vertical bias layer may be provided on top of the vertical bias layer 2b.

Furthermore, this embodiment has shown that the lower shield layer 16 and the lower conductive layer 1 provided  
5 separately. However, like the aforementioned embodiments 1 to 3, the lower shield layer 16 and lower conductive layer 1 may be a common layer. In this case, the lower conductive layer 1 is omitted. In addition, the upper shield 17 and the upper  
conductive layer 15 may be a common layer. In this case, the  
10 upper conductive layer 15 is omitted. This allows the gap between the top and bottom shield layers to be made smaller. Furthermore, an upper gap insulation layer may be provided between the upper conductive layer 15 and the shield layer 17 or a lower gap insulation layer may be provided between the lower  
15 shield layer 16 and the lower conductive layer 1.

Now, a fifth embodiment according to the present invention is described below. Figs. 34 - 37 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in  
20 the order in which they appear.

First, a layered body as shown in Fig. 16 is formed through the steps according to the aforementioned second embodiment shown in Figs. 13 - 19.

Then, as shown in Fig. 34, the photoresist 21 is removed.  
25 Then, on top of the exposed portion of the lower conductive layer 1 and the vertical bias layer 2b, formed and layered are the following layers. That is, the underlying layer for magnetic layer 8a, the magnetic layer 8b, the second non-magnetic layer 9,



the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are formed and layered in that order.

Then, as shown in Fig. 35, the photoresist 22 is provided to cover the region having no vertical bias layer 2b arranged immediately below the upper surface of the upper layer 7. With the photoresist 22 being employed as a mask, patterned by dry etching or like means are the underlying layer for magnetic layer 8a, the magnetic layer 8b, the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.

Then, as shown in Fig. 36, the photoresist 22 is removed to form the photoresist 23 on the upper layer 7 to cover the central portion of the upper layer 7. With the photoresist 23 being employed as a mask, patterned by dry etching or like means are the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7. Then, the periphery of the pattern of the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 is buried in the insulation layer 11, thereby forming a magnetoresistance effect element 34a on top of the lower shield layer 16.

Then, as shown in Fig. 37, after the photoresist 23 has been removed, the upper conductive layer 15 is deposited on the upper layer 7 and the insulation layer 11 to form a photoresist (not shown). Then, the upper conductive layer 15 is patterned by dry etching or like means and thereafter this photoresist is removed, on which the upper shield layer 17 is formed, thereby

forming a magneto-resistance effect head 64a.

Now, the structure of the magneto-resistance effect head 64a according to this embodiment is described below. As shown in Fig. 37, the magneto-resistance effect head 64a according to this embodiment has a different shape of the underlying layer for magnetic layer 8a and the magnetic layer 8b in comparison with the magneto-resistance effect head 63a according to the fourth embodiment shown in Fig. 31. In this embodiment, the underlying layer for magnetic layer 8a and the magnetic layer 8b are patterned to allow their end portion to be flush with the end portion of the underlying layer for vertical bias layer 2a and the vertical bias layer 2b and in contact with each other. In the magneto-resistance effect head 64a according to this embodiment, the structural operation and effect thereof are the same as those of the magneto-resistance effect head 63a according to the aforementioned fourth embodiment except the shape of the underlying layer for magnetic layer 8a and the magnetic layer 8b.

Incidentally, in this embodiment, it has been explained in which the non-magnetic layer 4 is patterned in conjunction with the fixed layer 5, the fixing layer 6b, and the upper layer 7. However, like the aforementioned fourth embodiment, the non-magnetic layer 4 may be extended as the magnetic layer 8b or may be patterned to be larger than the pattern of the fixed layer 5, the fixing layer 6b, and the upper layer 7 and smaller than the pattern of the free layer 3b.

Furthermore, the pattern of the second non-magnetic layer 9 may be extended further than that of the magnetic layer 8b or the pattern of the magnetic layer 8b may be extended further than

that of the non-magnetic layer 4.

In addition, in this embodiment, it has been explained in which the upper conductive layer 15 is patterned, however, the upper conductive layer 15 may not be patterned but extended.

5        Now, a sixth embodiment according to the present invention is described below. Figs. 38 - 42 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

10        First, a layered body as shown in Fig. 5 is formed through the steps according to the aforementioned first embodiment shown in Figs. 4 and 5.

Then, as shown in Fig. 38, the photoresist 20 is removed. Then, on the lower conductive layer 1, formed and layered in the  
15        following order are the underlying layer for magnetic layer 8a, the magnetic layer 8b, the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.

Then, as shown in Fig. 39, the photoresist 21 is provided  
20        to cover the region having no recessed portion 1a of the lower conductive layer 1 arranged immediately below the upper surface of the upper layer 7. With the photoresist 21 being employed as a mask, the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b,  
25        and the upper layer 7 are patterned. This allows the insulation layer 11 to bury therein the periphery of the second non-magnetic layer 9, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer.

Then, as shown in Fig. 40, the photoresist 21 is removed to form the photoresist 22 to cover the region having no recessed portion 1a immediately below the upper surface of the upper layer 7 and the insulation layer. And, the region covered with the photoresist 21 is included in the region to be covered by the photoresist 22.

Then, as shown in Fig. 41, with the photoresist 22 being employed as a mask, the insulation layer 11, the underlying layer for magnetic layer 8a, and the magnetic layer 8b are patterned by etching. Subsequently, the Underlying layer vertical bias 2a and the vertical bias layer 2b are formed successively, a second insulation layer 11b is formed on the vertical bias layer 2b, and a magneto-resistance effect element 34b is formed on the lower conductive layer 16.

Then, as shown in Fig. 41, the photoresist 22 is removed. Thereafter, on the upper layer 7, the insulation layer 11, and the second insulation layer 11b, the upper conductive layer 15 is deposited to form a photoresist (not shown). After the upper conductive layer 15 has been patterned by dry etching or like means, the photoresist is removed and the upper shield layer 17 is formed thereupon to form the magneto-resistance effect head 64b.

The magneto-resistance effect head 64b formed according to this embodiment has the same structure and operation as those of the magneto-resistance effect head 64a according to the fifth embodiment except that the insulation layers 11 and 11b are formed through two steps.

Now, described below is a seventh embodiment according to

the present invention. Figs. 43 - 49 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

5 First, as shown in Fig. 43, the lower shield layer 16 and the lower conductive layer 1 are successively formed on top of a substrate (not shown).

Then, as shown in Fig. 44, formed and layered in the following order are the underlying layer for fixing layer 6a, the  
10 fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9.

Then, as shown in Fig. 45, the photoresist 20 is patterned on the second non-magnetic layer 9. Then, the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the  
15 first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned by dry etching or like means. A pattern 29a is thereby formed which comprises the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second  
20 non-magnetic layer 9, which have been patterned.

Then, as shown in Fig. 46, the insulation layer 11 is formed to bury the pattern 29a therein. The insulation layer 11 is made equal in height to the pattern 29a near the pattern 29a but is slightly lower than the pattern 29a at a given distance  
25 from the pattern 29a, between which a smooth slope connects.

Then, as shown in Fig. 47, on the insulation layer 11, formed are the underlying layer for vertical bias layer 2a and the vertical bias layer 2b. And, the vertical bias layer 2b is

varied in thickness along the slope of the insulation layer 11, allowing the vertical bias layer 2b to be thick in thickness at a given distance from the pattern 29a and reduced in thickness with increasing proximity to the pattern 29a.

5           Then, as shown in Fig. 48, the photoresist 20 is removed to form the magnetic layer 8b and the upper layer 7 on the vertical bias layer 2b, thereby forming a magneto-resistance effect element 35a.

10           Then, as shown in Fig. 49, the upper conductive layer 15 is deposited on the upper layer 7 and the photoresist (not shown) is formed. After the upper conductive layer 15 has been patterned by dry etching or like means, the photoresist is removed to form the upper shield layer 17 thereupon, thus forming a magneto-resistance effect head 65a.

15           Now, the structure of the magneto-resistance effect head 65a according to this embodiment is described below. As shown in Fig. 49, the lower shield layer 16 is provided and the lower conductive layer 1 is provided on the lower shield layer 16. On top of the lower conductive layer 1, formed is the pattern 29a  
20   made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9, which have been patterned. The insulation layer 11 is arranged on the periphery of the pattern 29a, and the pattern 29a is buried in  
25   the insulation layer 11.

The upper surface of the insulation layer 11 is flush with that of the pattern 29a near the pattern 29a but is slightly lower than the upper surface of the pattern 29a at a given

distance from the pattern 29a, between which a smooth slope connects. The vertical bias layer 2b is provided on the insulation layer 11 along the topography of the upper surface of the insulation layer 11 in a manner such that at least part of the vertical bias layer 2b in the direction of its thickness is buried in the insulation layer 11. And, the vertical bias layer 2b is thick in thickness at a given distance from the pattern 29a and reduced in thickness with increasing proximity to the pattern 29a. On the vertical bias layer 2b and the pattern 29a, provided are the magnetic layer 8 and the upper layer 7.

On the upper layer 7, provided is the upper conductive layer 15, on top of which provided is the upper shield layer 17.

Now, the operation of the magneto-resistance effect head 65a according to this embodiment is described below. Application of an external magnetic field to the magneto-resistance effect head 65a will cause the magnetic field to be applied to the magnetic layer 8b via the vertical bias layer 2b. Subsequently, a vertical bias magnetic field is applied from the magnetic layer 8b to the free layer 3b via the second non-magnetic layer 9 by means of a magnetic coupling such as ferromagnetic coupling, anti-ferromagnetic coupling, or magneto-static coupling. And, the orientation of magnetization of the free layer 3b changes in accordance with the direction and magnitude of this magnetic field. Since the orientation of magnetization of the fixed layer 5 is pinned by the fixing layer 6b, a change occurs in orientation of magnetization between the fixed layer 5 and the free layer 3b, causing a change in electrical resistance of the non-magnetic layer 4. In this state, the lower conductive layer

1 and the upper conductive layer 15 allow a sense current to flow in the direction perpendicular to the non-magnetic layer 4 to measure the electrical resistance of the non-magnetic layer 4, thereby making it possible to detect the external magnetic field.

5 Now, an effect of this embodiment is described below. In the magneto-resistance effect head 65a according to this embodiment, a vertical bias magnetic field is applied to the free layer 3b from the vertical bias layer 2b through two steps of process, thereby assuring the application of the vertical bias  
10 magnetic field and facilitating the control of the amount of application of the magnetic field.

Incidentally, in this embodiment, it has been explained in which the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free  
15 layer 3b, and the second non-magnetic layer 9 are patterned in the same way. However, it is necessary to pattern at least the free layer 3b but not necessary to pattern the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4. In addition, the pattern of the  
20 underlying layer for fixing layer 6a may be extended further than that of the fixing layer 6b. The pattern of the fixing layer 6b may be extended further than that of the fixed layer 5. The pattern of the fixed layer 5 may be extended further than that of the non-magnetic layer 4. The pattern of the non-magnetic layer  
25 4 may be extended further than that of the free layer 3b.

Furthermore, this embodiment has shown that the upper surface of the insulation layer 11 is lower than that of the pattern of the free layer 3b. However, the upper surface of the insulation



layer 11 may be equal in height to the upper surface of the pattern of the free layer 3b and higher than the upper surface of the pattern of the free layer 3b.

Figs. 50 - 54 are fragmentary sectional views illustrating the structure of a magneto-resistance effect element according to a variation of this embodiment. A magneto-resistance effect element 35b shown in Fig. 50 is different from the magneto-resistance effect element 35a shown in Fig. 49 in that the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4 are not patterned. On the first non-magnetic layer 4, provided are the free layer 3b and the second non-magnetic layer 9, and these patterns are buried in the insulation layer 11. The magneto-resistance effect element 35b has the same structure as that of the magneto-resistance effect element 35a except the topography of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4. The operation of the magneto-resistance effect element 35b is also the same as that of the magneto-resistance effect element 35a.

In comparison with the magneto-resistance effect element 35a, the magneto-resistance effect element 35b is advantageous in that the etching process for the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4 can be omitted upon fabrication.

This variation has shown that the free layer 3b and the second non-magnetic layer 9 are patterned by etching of the first non-magnetic layer 4 using the photoresist as a mask. However, it is necessary to pattern at least the free layer 3b, and it can

be selected as appropriate which layers to pattern in the layered body made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer.

5           On the other hand, in a magneto-resistance effect element 35c shown in Fig. 51, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned.

10           Furthermore, in a magneto-resistance effect element 35d shown in Fig. 52, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned.

15           Still furthermore, in a magneto-resistance effect element 35e shown in Fig. 53, the pattern of the vertical bias layer 2b is provided apart from a pattern 29b made up of the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9. This makes it possible to prevent more positively the leakage of sense current to the vertical bias layer 2b. The structure and operation of the magneto-resistance effect element 35e is the same as those of the magneto-resistance effect element 20 35c shown in Fig. 51 except those mentioned in the foregoing.

25           This variation has shown that the free layer 3b and the second non-magnetic layer 9 are patterned. However, it is necessary to pattern at least the free layer 3b, but it can be selected as appropriate which layers to pattern in the layered body made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer.

          In addition, this variation has shown that the upper

surface of the insulation layer 11 is higher than that of the pattern of the free layer 3b. However, the upper surface of the insulation layer 11 may be generally equal in height to the upper surface of the pattern of the free layer 3b or lower than the upper surface of the pattern of the free layer 3b.

Furthermore, this variation has shown that the magnetic layer 8b is not patterned. However, at least part of the magnetic layer 8b is located near the vertical bias layer 2b just to allow a vertical bias magnetic field to be applied to the vertical bias layer 2b from the vertical bias layer 2b.

In a magneto-resistance effect element 35f shown in Fig. 54, the end portion of the pattern of the magnetic layer 8b sits on part of the vertical bias layer 2b.

In a magneto-resistance effect element 35g shown in Fig. 55, the end portion of the pattern of the magnetic layer 8b is in contact with that of the vertical bias layer 2b.

This variation has shown that the free layer 3b and the second non-magnetic layer 9 are patterned in the same way. However, like a magneto-resistance effect element 35h shown in Fig. 56, the second non-magnetic layer 9 may be extended over the vertical bias layer 2b.

In addition, like a magneto-resistance effect element 35i shown in Fig. 57, the second non-magnetic layer 9 may be extended over the insulation layer 11.

The magneto-resistance effect elements 35b, 35c, 35d, 35e, 35f, 35g, 35h, and 35i, shown in Figs. 50 - 57, can also be employed for the magneto-resistance effect head in the same way as the magneto-resistance effect element 35a.

Incidentally, in this embodiment, the lower shield layer 16 and the lower conductive layer 1 may be the same layer, and the upper shield layer 17 and the upper conductive layer 15 may be the same layer. In addition, an upper gap layer may be provided between the upper conductive layer 15 and the shield layer 17, and a lower gap layer may be provided between the lower shield layer 16 and the lower conductive layer 1.

In addition, the underlying layer for vertical bias layer 2a, the underlying layer for fixing layer 6a, the second non-magnetic layer 9, and the upper layer 7 may be omitted, and a protective layer for protecting the vertical bias layers may be provided on the vertical bias layer 2b.

Now, an eighth embodiment according to the present invention is described below. Figs. 58 - 64 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

First, as shown in Fig. 58, the lower shield layer 16 and the lower conductive layer 1 are successively formed on a substrate (not shown).

Then, as shown in Fig. 59, formed and layered in the following order are the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer.

Then, as shown in Fig. 60, the photoresist 20 having the opening portion 20a is formed on top of the second non-magnetic layer 9. Then, patterned are the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-

magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 by dry etching or like means. Thus, a pattern 29c is formed which is made up of the patterned the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the  
5 first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9, which have been patterned.

Then, as shown in Fig. 61, the insulation layer 11 is formed to bury the pattern 29c.

Then, as shown in Fig. 62, on the pattern 29c and the  
10 insulation layer 11, formed are the first magnetic layer 8, the third non-magnetic layer 13, the second magnetic layer 12, and the vertical bias layer 2b.

Then, as shown in Fig. 63, the photoresist 21 having the opening portion 21a is formed immediately above the patterned  
15 non-magnetic layer 9. Then, with the photoresist 21 being employed as a mask, the vertical bias layer 2b is patterned, thereby forming a magneto-resistance effect element 36a.

Then, as shown in Fig. 64, the photoresist 21 is removed. Then, the upper conductive layer 15 is deposited on the exposed  
20 portion of the second magnetic layer 12 and the pattern of the vertical bias layer 2b, and a photoresist (not shown) is formed to perform patterning by dry etching or like means. Thereafter, the photoresist is removed and the upper shield layer 17 is formed thereupon, thereby forming a magneto-resistance effect  
25 head 66a.

Now, the structure of the magneto-resistance effect head 66a according to this embodiment is described below. As shown in Fig. 64, the magneto-resistance effect head 66a is provided with

the lower shield layer 16, and the lower conductive layer 1 is provided on top of the lower shield layer 16. Thus, on top of the lower conductive layer 1, formed is the pattern 29c made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9, which have been patterned. The insulation layer 11 is arranged around the pattern 29c, and the pattern 29c is buried in the insulation layer 11.

On the pattern 29c and the insulation layer 11, provided are the first magnetic layer 8, a third non-magnetic layer 13, and a second magnetic layer 12. On top of the second magnetic layer 12, the vertical bias layer 2b is provided so as not to be disposed immediately above the pattern 29c.

In addition, the third non-magnetic layer 13 allows the component material and the film thickness thereof to control the magnetic coupling between the second magnetic layer 12 and the magnetic layer 8. Materials forming the third non-magnetic layer 13 include a single material of one type, a mixture of materials of two or more types, a compound of two or more types, or a multi-layered film formed of materials of two or more types, which are selected from the group consisting of Ti, V, Cr, Co, Cu, Zn, Y, Zr, Nb, Mo, Tc, Ru, Rh, Pd, Ag, Hf, Ta, W, Re, Os, Ir, Pt, Au, Si, Al, Ta, Pt, and Ni. In particular, Ru and Cr are favorable.

On the other hand, materials forming the second magnetic layer 12 include a single material of one type, a mixture of materials of two or more types, or a multi-layered film formed of

materials of two or more types, which are selected from the group consisting of alloys or amorphous magnetic materials such as NiFe, Co, CoFe, NiFeCo, FeCo, CoFeB, CoZrMo, CoZrNb, CoZr, CoZrTa, CoHf, CoTa, CoTaHf, CoNbHf, CoZrNb, CoHfPd, CoTaZrNb, and CoZrMoNi. In particular, NiFe, Co, CoFe, NiFeCo, and FeCo are favorable. In addition, as an additive element, one or more types of elements can be used which are selected from the group consisting of Ta, Hf, Zr, W, Cr, Ti, Mo, Pt, Ni, Ir, Cu, Ag, Co, Zn, Ru, Rh, Re, Au, Os, Pd, Nb, and V.

Now, the operation of the magneto-resistance effect head 66a according to this embodiment is described below. When an external magnetic field is applied to the magneto-resistance effect head 66a, the magnetic field is applied to the second magnetic layer 12 via the vertical bias layer 2b. Subsequently, a vertical bias magnetic field is applied from the second magnetic layer 12 to the magnetic layer 8b via the third non-magnetic layer 13 by means of magnetic coupling such as ferromagnetic coupling, anti-ferromagnetic coupling, or magneto-static coupling. Furthermore, the vertical bias magnetic field is applied from the magnetic layer 8 to the free layer 3b via the second non-magnetic layer 9 by means of magnetic coupling such as ferromagnetic coupling, anti-ferromagnetic coupling, or magneto-static coupling.

The orientation of magnetization of the free layer 3b changes in accordance with the direction and magnitude of this magnetic field. Since the orientation of magnetization of the fixed layer 5 is pinned by the fixing layer 6b, a change occurs in orientation of magnetization between the fixed layer 5 and the

free layer 3b, causing a change in electrical resistance of the non-magnetic layer 4. In this state, the lower conductive layer 1 and the upper conductive layer 15 allow a sense current to flow in the direction perpendicular to the non-magnetic layer 4 to  
5 measure the electrical resistance of the non-magnetic layer 4, thereby making it possible to detect the external magnetic field.

Now, an effect of this embodiment is described below. In the magneto-resistance effect head 65a according to this embodiment, a vertical bias magnetic field is applied to the free  
10 layer 3b from the vertical bias layer 2b through three steps of process, thereby assuring the application of the vertical bias magnetic field and facilitating the control of the amount of application of the magnetic field.

Another advantage of the magneto-resistance effect head  
15 65a is provided when the layered film made up of the magnetic layer 8, the third non-magnetic layer 13, and the second magnetic layer 12 produces a strong anti-ferromagnetic coupling between the magnetic layer 8 and the second magnetic layer 12. The advantage is also provided when the magnetization of the magnetic  
20 layer 8 (the product of the saturation magnetization and the film thickness) is made substantially equal to that of the second magnetic layer 12. In this case, the foregoing layered film is turned to a merged film having effectively no magnetization, thus providing no sensitivity to the magnetic field of an external  
25 magnetic field applied. For this reason, in this case, only the free layer 3b, in the structure of Fig. 64, has sensitivity to an external magnetic field. Thus, the width of the tracks is determined only by the pattern width of the free layer 3b when



the magneto-resistance effect head 65a functions as the read head. This is advantageous in making a narrow-track head. Incidentally, even in this case, a vertical bias magnetic field is applied precisely to the free layer 3b through the aforementioned process.

- 5 In addition, that the magnetization of the magnetic layer 8 is substantially equal to that of the second magnetic layer 12 means that they are equal to each other to the degree that the aforementioned effect is recognized.

Incidentally, in this embodiment, the underlying layer for  
10 fixing layer 6a, the second non-magnetic layer 9, the third non-magnetic layer 13, and the upper layer 7 may be omitted. In addition, an underlying layer for vertical bias layer may be provided on the lower portion of the vertical bias layer 2b. In some cases, a protective layer for protecting a vertical bias  
15 layer is provided on the vertical bias layer 2b, and an upper layer is provided on the second magnetic layer 12.

Furthermore, in this embodiment, it has been explained in which the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free  
20 layer 3b, and the second non-magnetic layer 9 are patterned in the same way. However, it is necessary to pattern at least the free layer 3b but not necessary to pattern the layered film made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4. In  
25 addition, the pattern of the underlying layer for fixing layer 6a may be extended further than that of the fixing layer 6b. The pattern of the fixing layer 6b may be extended further than that of the fixed layer 5. The pattern of the fixed layer 5 may be

extended further than that of the non-magnetic layer 4. The pattern of the non-magnetic layer 4 may be extended further than that of the free layer 3b. In addition, this embodiment has shown such that the upper surface of the insulation layer 11 is  
5 equal in height to that of the pattern of the free layer 3b. However, the upper surface of the insulation layer 11 may be lower than that of the pattern of the free layer 3b or higher than the upper surface of the pattern of the free layer 3b. Furthermore, Fig. 64 has shown that the second non-magnetic layer  
10 9 and the free layer 3b are patterned in the same way. However, the pattern of the second non-magnetic layer 9 may be extended further than that of the free layer 3b.

Figs. 65 - 66 are fragmentary sectional views illustrating the structure of a magneto-resistance effect element according to a variation of this embodiment. With reference to Fig. 64, it  
15 has been shown in which the first magnetic layer 8, the third non-magnetic layer 13, and the second magnetic layer 12 are not patterned. However, in a magneto-resistance effect element 36b shown in Fig. 65, the end portion of patterns of the magnetic  
20 layer 8, the third non-magnetic layer 13, and the second magnetic layer 12 is arranged under the pattern of the vertical bias layer 2b.

In addition, in the magneto-resistance effect element 36c shown in Fig. 66, the end portion of patterns of the magnetic  
25 layer 8, the third non-magnetic layer 13, and the second magnetic layer 12 are in contact with the end portion of the pattern of the vertical bias layer 2b. Incidentally, the magneto-resistance effect elements 36b and 36c can also be employed for the magneto-

resistance effect head, like the magneto-resistance effect element 36a.

Now, a ninth embodiment of the present invention is described below. Figs. 67 - 70 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

First, a structure body as shown in Fig. 61 is formed through the steps, shown in Figs. 58 - 61, according to the aforementioned eighth embodiment.

Then, as shown in Fig. 67, the photoresist 20 is removed, and the photoresist 21 is formed to cover the peripheral region of the second non-magnetic layer 9 and the second non-magnetic layer 9 in the insulation layer 11.

Then, as shown in Fig. 68, with the photoresist 21 being employed as a mask, a recessed portion 11a is formed in the insulation layer 11, and the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are formed so as to be buried in the recessed portion 11a.

Then, as shown in Fig. 69, the photoresist 21 is removed to form the first magnetic layer 8, the third non-magnetic layer 13, and the second magnetic layer 12 in that order, thereby forming a magneto-resistance effect element 37a.

Then, as shown in Fig. 70, the upper conductive layer 15 is deposited on the second magnetic layer 12 and then a photoresist (not shown) is formed. With this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Thereafter, the photoresist is

removed and the upper shield layer 17 is formed thereupon,  
thereby forming a magneto-resistance effect head 67a.

Now, the structure of the magneto-resistance effect head  
67a according to this embodiment is described below. The  
5 magneto-resistance effect head 67a is provided with the lower  
shield layer 16, and the lower conductive layer 1 is provided on  
the lower shield layer 16. Then, formed on top of the lower  
conductive layer 1 is the pattern in which the underlying layer  
for fixing layer 6a patterned on the fixing layer 6b, the fixed  
10 layer 5, non-magnetic layer 4, the free layer 3b, and the second  
non-magnetic layer 9 are layered in that order, and this pattern  
is buried in the insulation layer 11. As shown in Fig. 70, the  
insulation layer 11 has the recessed portion 11a on the upper  
surface thereof, and the underlying layer for vertical bias layer  
15 2a and the vertical bias layer 2b are formed so as to be buried  
in the recessed portion 11a. Then, on the second non-magnetic  
layer 9, the insulation layer 11, and the vertical bias layer 2b,  
formed are the magnetic layer 8, the third non-magnetic layer 13,  
and the second magnetic layer 12. Furthermore, the patterned  
20 upper conductive layer 15 is provided on the second magnetic  
layer 12, and the upper shield layer 17 is provided on the  
pattern of the second magnetic layer 12 and the upper conductive  
layer 15.

Now, a tenth embodiment according to the present invention  
25 is described below. Figs. 71 - 76 are fragmentary sectional  
views illustrating the steps of a method for fabricating a  
magneto-resistance effect head according to this embodiment in  
the order in which they appear.

First, as shown in Fig. 71, on a substrate (not shown), formed are the lower shield layer 16 and the lower conductive layer 1.

Then, as shown in Fig. 72, the following layers are formed and layered on the lower conductive layer 1. That is, the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, the second non-magnetic layer 9, the first magnetic layer 8, the third non-magnetic layer 13, the second magnetic layer 12, the underlying layer for vertical bias layer 2a, and the vertical bias layer 2b are formed and layered in that order.

Then, as shown in Fig. 73, the photoresist 20 is patterned on the vertical bias layer 2b.

Then, as shown in Fig. 74, with the photoresist 20 being employed as a mask, etched by dry etching or like means and thereby patterned are the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the non-magnetic layer 4, the free layer 3b, the second non-magnetic layer 9, the magnetic layer 8, the third non-magnetic layer 13, the second magnetic layer 12, the underlying layer for vertical bias layer 2a, and the vertical bias layer 2b. Thus, a pattern 29d is formed which is made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the non-magnetic layer 4, the free layer 3b, the second non-magnetic layer 9, the magnetic layer 8, the third non-magnetic layer 13, the second magnetic layer 12, the underlying layer for vertical bias layer 2a, and the vertical bias layer 2b.

Then, as shown in Fig. 75, the insulation layer 11 is

formed to bury the pattern 29d therein, thereby forming the magneto-resistance effect element 38a.

Then, as shown in Fig. 76, the photoresist 20 is removed, and the upper conductive layer 15 is formed on the vertical bias layer 12 and the insulation layer 11 to form a photoresist (not shown). Then, with this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Then, the photoresist is removed to form the upper shield layer 17 thereupon, thus forming a magneto-resistance effect head.

Now, the structure of the magneto-resistance effect head according to this embodiment is described below. As shown in Fig. 76, the magneto-resistance effect head is provided with a lower shield layer (not shown), and the lower conductive layer 1 is provided on a lower shield layer. On top of the lower conductive layer 1, provided is the pattern 29d made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, non-magnetic layer 4, the free layer 3b, the second non-magnetic layer 9, the first magnetic layer 8, the third non-magnetic layer 13, the second magnetic layer 12, the underlying layer for vertical bias layer 2a, and the vertical bias layer 2b, which have been patterned. The pattern 29d is buried in the insulation layer 11, and the vertical bias layer 2b of the pattern 29d is exposed on the upper surface of the insulation layer 11. In addition, the upper conductive layer 15, which has been patterned, is provided on top of the pattern 29d and the insulation layer 11, and the upper shield layer 17 is provided on the upper conductive layer 15 and the insulation layer 11.

Now, the operation of the magneto-resistance effect head

according to this embodiment is described below. The magnetic field applied to the magneto-resistance effect head is applied to the second magnetic layer 12 via the vertical bias layer 2b.

Then, the vertical bias magnetic field is applied to the first  
5 magnetic layer 8 from the second magnetic layer 12 via the third non-magnetic layer 13 by means of magnetic coupling such as ferromagnetic coupling, antiferromagnetic coupling, or magneto-static coupling. Furthermore, the vertical bias magnetic field is applied to the free layer 3b from the first magnetic layer 8  
10 via the second non-magnetic layer 9 by means of magnetic coupling such as ferromagnetic coupling, antiferromagnetic coupling, or magneto-static coupling.

The third non-magnetic layer 13 allows the component material and the film thickness thereof to control the magnetic  
15 coupling between the second magnetic layer 12 and the magnetic layer 8. In addition, the second non-magnetic layer 9 allows the component material and the film thickness thereof to control the magnetic coupling between the magnetic layer 8 and the free layer 3b. As described above, a vertical bias magnetic field is  
20 applied to the free layer 3b from the vertical bias layer 2b through three steps of process, thereby assuring the application of the vertical bias magnetic field and facilitating the control of the magnetic field applied.

Incidentally, the underlying layer for fixing layer 6a,  
25 the second non-magnetic layer 9, the third non-magnetic layer 13, and the underlying layer for vertical bias layer 2a can be omitted. Incidentally, a protective layer for protecting the vertical bias layer 2b may be provided on the vertical bias layer

2b, while an upper layer may be provided on the second magnetic layer 12.

Fig. 77 is a fragmentary sectional view illustrating the structure of a magneto-resistance effect element 38b according to a variation of this embodiment. The magneto-resistance effect element 38b is provided with the lower conductive layer 1 on a substrate (not shown). On top of the lower conductive layer 1, provided are the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, non-magnetic layer 4, the free layer 3b, the second non-magnetic layer 9, the first magnetic layer 8, the underlying layer for vertical bias layer 2a, and the vertical bias layer 2b. And, these layers have been patterned and buried in the insulation layer 11. The vertical bias layer 2b is exposed on the upper surface of the insulation layer 11.

First, the vertical bias magnetic field applied to the magneto-resistance effect element 38b is applied to the magnetic layer 8 via the vertical bias layer 2b. Then, the vertical bias magnetic field is applied to the free layer 3b from the first magnetic layer 8 via the second non-magnetic layer 9 by means of magnetic coupling such as ferromagnetic coupling, antiferromagnetic coupling, or magneto-static coupling. And, the second non-magnetic layer 9 allows the component material and the film thickness thereof to control the magnetic coupling between the magnetic layer 8 and the free layer 3b.

As described above, a vertical bias magnetic field is applied to the free layer 3b from the vertical bias layer 2b through two steps of process, thereby assuring the application of the vertical bias magnetic field and facilitating the control of



the amount of the magnetic field applied.

Incidentally, in this embodiment, it has been explained in which the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned in the same way. However, it is necessary to pattern at least the free layer 3b but not necessary to pattern the layered film made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the non-magnetic layer 4. In addition, the pattern of the underlying layer for fixing layer 6a may be extended further than that of the fixing layer 6b. The pattern of the fixing layer 6b may be extended further than that of the fixed layer 5. The pattern of the fixed layer 5 may be extended further than that of the non-magnetic layer 4. The pattern of the first non-magnetic layer 4 may be extended further than that of the free layer 3b.

Now, an eleventh embodiment according to the present invention is described below. Figs. 78 - 87 are fragmentary sectional views illustrating the steps of a method for fabricating a magneto-resistance effect head according to this embodiment in the order in which they appear.

First, as shown in Fig. 78, the lower shield layer 16 and the lower conductive layer 1 are successively formed on top of a substrate (not shown).

Then, as shown in Fig. 79, the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are formed and layered in that order on the lower

conductive layer 1.

Then, as shown in Fig. 80, the photoresist 20 is patterned on the second non-magnetic layer 9. Then, the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the  
5 first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned by dry etching or like means, thereby forming a pattern 29e made up of these layers.

Then, as shown in Fig. 81, the insulation layer 11 is formed around the pattern 29e to bury the pattern 29e therein.  
10 And, the insulation layer 11 is made equal in height to the pattern 29e near the pattern 29e but is slightly lower than the pattern 29e at a given distance from the pattern 29e, between which a smooth slope connects.

Then, as shown in Fig. 82, on the insulation layer 11,  
15 formed are the underlying layer for vertical bias layer 2a and the vertical bias layer 2b. The vertical bias layer 2b is varied in thickness along the slope of the insulation layer 11, allowing the vertical bias layer 2b to be thick in thickness at a given distance from the pattern 29e and reduced in thickness with  
20 increasing proximity to the pattern 29e.

Then, as shown in Fig. 83, the photoresist 20 is removed to form the first magnetic layer 8 and a fourth magnetic layer 18 on the second non-magnetic layer 9 and the vertical bias layer 2b.

Then, as shown in Fig. 84, a second free layer 19, a fifth  
25 non-magnetic layer 25, a second fixed layer 26, a second fixing layer 27, and the upper layer 7 are formed in that order.

Then, as shown in Fig. 85, the photoresist 21 is formed to cover the region that matches the pattern 29e on the upper layer

7. With the photoresist 21 being employed as a mask, the fourth non-magnetic layer 18, the second free layer 19, the fifth non-magnetic layer 20, the second fixed layer 26, the second fixing layer 27, and the upper layer 7 are patterned. Formed thereby is  
5 a pattern 29f made up of the fourth non-magnetic layer 18, the second free layer 19, the fifth non-magnetic layer 20, the second fixed layer 26, the second fixing layer 27, and the upper layer 7.

Then, as shown in Fig. 86, around the pattern 29f, the insulation layer 11b is formed to bury pattern 29f therein,  
10 thereby providing a magneto-resistance effect element 39a formed on the lower shield layer 16.

Then, as shown in Fig. 87, the photoresist 21 is removed, and the upper conductive layer 15 is deposited on the upper layer 7 and the insulation layer 11b to form a photoresist (not shown).  
15 With this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Thereafter, the photoresist is removed and the upper shield layer 17 is formed thereupon, thus forming a magneto-resistance effect head 69a.

20 Now, the structure of the magneto-resistance effect element 39a according to this embodiment is described below. As shown in Fig. 87, the magneto-resistance effect element 39a is adapted that the non-magnetic layer, the free layer, the non-magnetic layer, the fixed layer, and the fixing layer are formed  
25 to be vertically symmetric with respect to the second non-magnetic layer 8b to which a vertical bias magnetic field is applied from the underlying layer for vertical bias layer 2a.

The magneto-resistance effect element 39a is provided with

the lower shield layer 16, and the lower conductive layer 1 is provided on the lower shield layer 16. On top of the lower conductive layer 1, formed is the pattern 29e made up of the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9, which have been patterned. The pattern 29e is buried in the insulation layer 11.

The upper surface of the insulation layer 11 is generally flush with that of the pattern 29e near the pattern 29e but is slightly lower than the upper surface of the pattern 29e at a given distance from the pattern 29e. The pattern of the underlying layer for vertical bias layer 2a and the vertical bias layer 2b is provided to allow at least part thereof in the direction of film thickness to be buried in the insulation layer 11. The second non-magnetic layer 8 is provided on the pattern 29e and the vertical bias layer 2b.

On top of the second non-magnetic layer 8, the pattern 29f is provided which is made up of the fourth magnetic layer 18, the second free layer 19, the fifth non-magnetic layer 25, the second fixed layer 26, the second fixing layer 27, and the upper layer 7, which have been patterned, with the pattern 29f being buried in the insulation layer 11b. In addition, the upper conductive layer 15 and the upper shield layer 17 are provided on the pattern 29f and the insulation layer 11b.

Now, the operation of the magneto-resistance effect element 39a according to this embodiment is described below. When a sensor containing the magneto-resistance effect element 39a is subjected to an external magnetic field, the second free

layer 19, like the free layer 3b, serves as a magnetic layer which changes its orientation of magnetization in accordance with the orientation and magnitude of the magnetic field. The fifth non-magnetic layer 25 is disposed between the second free layer 19 and the second fixed layer 26, and varies in electrical resistance in accordance with the angle between the orientation of magnetization of the second free layer and that of the second fixed layer 26. The orientation of magnetization of the second fixed layer 26 is pinned by the second fixing layer 27. Thus, a change in orientation of magnetization of the free layer in accordance with the orientation and magnitude of an external magnetic field would cause a change to occur between the orientation of magnetization of the fixed layer, the orientation of which is pinned, and that of the free layer. This results in a change in resistance of the fifth non-magnetic layer 25.

In the magneto-resistance effect element 39a, the amount of a change in electrical resistance produced upon conducting a sense current from the lower conductive layer 1 to the upper conductive layer 15 is equal to the sum of a change in electrical resistance of the pattern 29e located below the magnetic layer 8 and a change in electrical resistance of the pattern 29f located above the magnetic layer 8.

Generally, in the magneto-resistance effect element, the free layer is unavoidably subjected to the influence of a circular electric magnetic field caused by a current flowing perpendicularly to the film surface. However, in the magneto-resistance effect element 39a according to this embodiment, the influence of the electric magnetic field to which the free layer

3b is subjected is opposite to that of the electric magnetic field to which the second free layer 19 is subjected, thereby canceling out the influences as a whole. Thus, it is made possible to significantly reduce the influence of the electric magnetic field.

In addition, in the magneto-resistance effect element 39a, the vertical bias magnetic field applied is first applied to the second magnetic layer 8 via the vertical bias layer 2b. Then, the vertical bias magnetic field is applied to the free layer 3b from the second magnetic layer 8 via the second non-magnetic layer 9 and to the second free layer 19 through the fourth non-magnetic layer 18. The second non-magnetic layer 9 controls the magnetic coupling between the second magnetic layer 8b and the free layer 3b by the component material and film thickness thereof, while the fourth non-magnetic layer 18 controls the magnetic coupling between the magnetic layer 8b and the second free layer 19 by the component material and film thickness thereof. As described above, a vertical bias magnetic field is applied to the free layer 3b and the second free layer 19 from the vertical bias layer 2b through two steps of process, thereby assuring the application of the vertical bias magnetic field and facilitating the control of the amount of application of the magnetic field.

Incidentally, in this embodiment, the underlying layer for vertical bias layer 2a, the underlying layer for fixing layer 6a, the second non-magnetic layer 9, the fourth magnetic layer 18, and the upper layer 7 can be omitted. Furthermore, in some cases, a protective layer for protecting the vertical bias layer may be

provided on the vertical bias layer 2b.

In addition, in this embodiment, it has been explained in which the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, the first non-magnetic layer 4, the free layer 3b, and the second non-magnetic layer 9 are patterned in the same way. However, it is necessary to pattern at least the free layer 3b but not necessary to pattern the underlying layer for fixing layer 6a, the fixing layer 6b, the fixed layer 5, and the first non-magnetic layer 4. Furthermore, the pattern of the underlying layer for fixing layer 6a may be extended further than that of the fixing layer 6b. The pattern of the fixing layer 6b may be extended further than that of the fixed layer 5. The pattern of the fixed layer 5 may be extended further than that of the non-magnetic layer 4. The pattern of the first non-magnetic layer 4 may be extended further than that of the free layer 3b.

Still furthermore, this embodiment has shown that the upper surface of the insulation layer 11 is lower than that of the pattern of the free layer 3b at a given distance from the pattern 29e or 29f. However, the upper surface of the insulation layer 11 may be equal in height to the upper surface of the pattern of the free layer 3b or higher than the upper surface of the pattern of the free layer 3b. Furthermore, the pattern of the vertical bias layer 2b may be spaced apart from the pattern of the free layer 3b and that of the second free layer 19. In addition, the fourth magnetic layer 18 may be patterned in conjunction with the second free layer 19 and extended further than the pattern of the second free layer 19. Furthermore, the pattern of the second non-magnetic layer 9 may be extended

further than that of the free layer 3b.

Figs. 88 - 90 are fragmentary sectional views illustrating the structure of a magneto-resistance effect element according to a variation of this embodiment. Fig. 88 shows that fourth

5 magnetic layer 18 is not patterned.

In addition, Fig. 89 shows that the upper surface of the insulation layer 11 is higher than that of the pattern of the free layer 3b.

Furthermore, Fig. 90 shows that the pattern of the  
10 vertical bias layer 2b is spaced apart from that of the free layer 3b and the second free layer 19. The magneto-resistance effect element shown in Figs. 88 - 90 can also be employed for the magneto-resistance effect head.

Now, a twelfth embodiment according to the present  
15 invention is described below. Figs. 91 - 94 are fragmentary sectional views illustrating the structure of a magneto-resistance effect head according to this embodiment.

First, a layered body as shown in Fig. 6 is formed through the steps, shown in Figs. 4 - 6, according to the aforementioned  
20 first embodiment.

Then, as shown in Fig. 91, on the lower conductive layer 1 and the vertical bias layer 2b, layered in sequence are a second underlying layer for magnetic layer 12a, a second magnetic layer 12b, the third non-magnetic layer 13, the second magnetic layer 8,  
25 the second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.

Then, as shown in Fig. 92, a photoresist 21 is formed at



the central portion of the region where no recessed portion 1a of the lower conductive layer 1 is formed on the upper layer 7.

Then, as shown in Fig. 93, the second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 are etched by dry etching or like means. Then, the portion removed by the etching is buried in the insulation layer 11 and thus a magneto-resistance effect element 39b is formed.

Then, as shown in Fig. 94, the photoresist 21 is removed, and the upper conductive layer 15 is deposited to form a photoresist (not shown). With this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Thereafter, this photoresist is removed and the upper shield layer 17 is formed thereupon, thus forming a magneto-resistance effect head 69b.

Now, the structure of the magneto-resistance effect head 69b according to this embodiment is described below. As shown in Fig. 94, the magneto-resistance effect head 69b is provided with the lower shield layer 16, while the lower conductive layer 1 is provided on the lower shield layer 16. The recessed portion 1a is provided on the upper surface of the lower conductive layer 1, and the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are provided so as to be in the recessed portion 1a. On the lower conductive layer and the vertical bias layer 2b, provided are the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8. A pattern made up of the second non-magnetic layer 9, the free layer 3b, the non-

magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 is formed immediately above the portion surrounded by the pattern of the two vertical bias layers on the magnetic layer 8.

5 In this embodiment, it has been shown in which the second non-magnetic layer 9 is patterned in conjunction with the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7. However, the second non-magnetic layer 9 may be extended like the pattern of the magnetic layer 8. Alternatively, the second non-magnetic layer 9 may be extended further than the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7, or may be smaller than the pattern of the magnetic layer 8.

10 In addition, the underlying layer for vertical bias layer 2a, the second non-Underlying layer for magnetic layer 12a, and the upper layer 7 can be omitted. A protective layer for protecting the vertical bias layer can be provided on the upper of the vertical bias layer 2b. Furthermore, the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 do not always have to extend as shown in Fig. 94.

15 Figs. 95 and Fig. 96 are fragmentary sectional views illustrating the structure of a magneto-resistance effect element according to a variation of this embodiment. Fig. 95 shows that the end portion of the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 is in contact with that of the pattern of the vertical bias layer 2b.

In addition, Fig. 96 shows that the end portion of the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 sits on the pattern of the vertical bias layer 2b.

In addition, the pattern of the second magnetic layer 12b may be larger than that of the third non-magnetic layer 13, and the pattern of the third non-magnetic layer 13 may be larger than the pattern of the magnetic layer 8b.

Now, a thirteenth embodiment according to the present invention is described below. Figs. 97 - 102 are fragmentary sectional views illustrating the structure of a magneto-resistance effect head according to this embodiment.

First, as shown in Fig. 97, the lower shield layer 16 and the lower conductive layer 1 are formed successively on a substrate (not shown).

Then, as shown in Fig. 98, the underlying layer for vertical bias layer 2a and the vertical bias layer 2b are deposited on the lower conductive layer 1.

Then, as shown in Fig. 99, layered sequentially are the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, the magnetic layer 8, the second non-magnetic layer 9, the underlying layer for free layer 3a, the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7.

Then, as shown in Fig. 100, the photoresist 21 is patterned on the upper layer 7.

Then, as shown in Fig. 101, with the photoresist 21 being

employed as a mask, the second non-magnetic layer 9, the free layer 3b, the first non-magnetic layer 4, the fixed layer 5, the fixing layer 6b and the upper layer 7 are etched by dry etching or like means. Thereafter, the portion removed by the etching is  
5 buried in the insulation layer 11 and thus a magneto-resistance effect element 39c is formed.

Then, as shown in Fig. 102, the photoresist 20 is removed, and the upper conductive layer 15 is deposited on the insulation layer 11 and the upper layer 7 to form a photoresist (not shown).  
10 With this photoresist being employed as a mask, the upper conductive layer 15 is patterned by dry etching or like means. Then, this photoresist is removed and the upper shield layer 17 is formed on the upper conductive layer 15, thus forming a magneto-resistance effect head 69c.

15 Now, the structure of the magneto-resistance effect head 69c according to this embodiment is described below. As shown in Fig. 102, the magneto-resistance effect head 69c has the lower conductive layer 1 provided on the lower shield layer 16. The underlying layer for vertical bias layer 2a and the vertical bias  
20 layer 2b are provided thereupon. Further formed thereupon are the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the magnetic layer 8. On the magnetic layer 8, provided are the second non-magnetic layer 9, the free layer 3b, the non-magnetic  
25 layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7, which have been patterned and buried in the insulation layer 11. In addition, the upper conductive layer 15 is provided on the upper layer 7 and the insulation layer 11, upon which

provided is the upper shield layer.

In this embodiment, it has been shown in which the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 are patterned. However, the second non-magnetic layer 9 may extend like the pattern of the first magnetic layer 8. Alternatively, the second non-magnetic layer 9 may be extended further than the pattern of the free layer 3b, the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7 and may be smaller than the pattern of the magnetic layer 8.

In addition, the vertical bias film underlying layer 2a, the second non-underlying layer for magnetic layer 12a, and the upper layer 7 can be omitted. Furthermore, a protective layer for protecting the vertical bias layer can be provided above the vertical bias layer 2b. Furthermore, the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 do not always have to extend.

Figs. 103 and 104 are fragmentary sectional views illustrating the structure of a magneto-resistance effect element according to a variation of this embodiment. Fig. 103 shows that the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 are patterned.

In addition, Fig. 104 shows that the second underlying layer for magnetic layer 12a, the second magnetic layer 12b, the third non-magnetic layer 13, and the first magnetic layer 8 are

patterned to be generally equal in size to the pattern of the second non-magnetic layer 9, the free layer 3b, the first the non-magnetic layer 4, the fixed layer 5, the fixing layer 6b, and the upper layer 7. The magneto-resistance effect element shown in Figs. 103 and 104 can also be employed for the magneto-resistance effect head.

Furthermore, the pattern of the second magnetic layer 12b may be larger than that of the third non-magnetic layer 13, and the pattern of the third non-magnetic layer 13 may be larger than that of the first magnetic layer 8b.

Now, shown below is an application embodiment of the magneto-resistance effect element according to the present invention to a read/write head and a read/write system. Fig. 105 shows a schematic view illustrating a magnetic read/write head according to this embodiment. In this magnetic read/write head (a read/write element portion 130), provided on a substrate 42 is a read head 45, including the aforementioned magneto-resistance effect head as part thereof, for reading a signal from a storage medium. In addition, on the read head 45, there is provided a write head 46, comprising a magnetic pole 43, a plurality of coils 41, and an upper magnetic pole 44, for writing a signal onto the storage medium. In this case, the magnetic pole 43 may be commonly used as the upper shield layer or may be provided separately. As shown in Fig. 105, the magneto-sensitive portion of the read head 45 and the magnetic gap of the write head are formed to overlap each other on the same slider, thereby making it possible to simultaneously position them on the same track. And, the write head 46 applies a magnetic field to a storage

medium (not shown) to write data thereon, and the read head 45 reads data stored in this storage medium. This read/write head is machined into a slider to be mounted on a magnetic read/write device.

5           Fig. 106 is a schematic view illustrating the structure of a magneto-resistance transducer system, comprising the magnetic read/write head shown in Fig. 105, according to this embodiment. This magneto-resistance transducer system is provided with the read/write element portion 130 (a magnetic read/write head)  
10   formed in a board 129 constituting the slider and is protected by a protective film 132. For example, the board 129 is formed of  $\text{Al}_2\text{O}_3$ -TiC composite ceramic or the like, while the protective film 132 is formed of diamond-like carbon.

          The read/write element portion 130 is provided with  
15   electrode terminals 131a connected to the write element portion (the write head) and electrode terminals 131b connected to the read element portion (the read head). The electrode terminal 131a applies a drive electric current to the write element portion and is connected to an electric current drive circuit 133  
20   for causing write operation to occur. In addition, the electrode terminal 131b is connected to an electric current generator circuit 134 for conducting a sense current through the read element portion. The electrode terminal 131b is also connected to a data read circuit 135 for detecting a voltage change caused  
25   by a change in specific resistance of the read element portion as a function of an applied magnetic field to read data information stored on the storage medium. As described above, the magneto-resistance transducer system comprises the read/write element

portion 130, the electric current generator circuit 134, and the data read circuit 135.

Fig. 107 is a schematic view illustrating an embodiment of a magnetic storage system employing the magneto-resistance transducer system shown in Fig. 106. This magnetic storage system comprises a magneto-resistance transducer system having a magnetic read/write head 103, sense current detecting means 107, and a controller 108. The magnetic storage system also comprises a magnetic storage medium 102 having a plurality of tracks for storing data, a first actuator 106 having a VCM (Voice Coil Motor) for moving the magnetic read/write head 103 to a given position on the magnetic storage medium 102, and a second actuator 101 having a motor for rotating the magnetic storage medium 102. In addition, the magnetic read/write head 103 is supported by a suspension 104 and an arm 105.

Fig. 108 is a perspective view illustrating a specific embodiment of the magnetic storage system. In this embodiment, a read head 51 and a write head 50 are formed on a board 52 that also serves as a head slider and positioned on a storage medium 53 for read operation. The storage medium 53 rotates and the head slider moves relatively thereto  $0.2 \mu\text{m}$  or less above the storage medium 53 or in contact therewith. This mechanism allows the read head 51 to be set to where the read head 51 can read a magnetic signal stored on the storage medium 53 from a leak magnetic field 54.

As the magnetic memory system of the present invention, it is possible to employ hard disk devices, flexible disk devices, and magnetic tape units. The hard disk devices include a fixed



disk device that allows no disks to be replaced and a disk device that allows disks to be replaced.

Now, described below is a prototype of a magnetic memory device fabricated according to the present invention. The magnetic memory device comprises three magnetic disks (magnetic storage media) on the base and houses, on the reverse side of the base, a head drive circuit, a signal processing circuit, and an input/output interface. The magnetic memory device is connected to the outside by a 32-bit bus line. The magnetic memory device is provided with six heads arranged on both sides of a magnetic disk, a rotary actuator for driving the heads (actuator means), and a drive circuit, a control circuit, and a motor directly connected to the disk rotating for use therewith. The disk is 63mm in diameter and uses the range from 10mm to 57mm in diameter as the data storage surface. A buried servo scheme is employed and thereby no servo surface is prevent, thus making it possible to provide a high density. It is possible to directly connect this device to a small computer as an auxiliary memory device. The input/output interface is provided with a cash memory, corresponding to a bus line having transfer speeds within the range of 5 to 20MB per second. It is also possible to provide an external controller having a plurality of the devices connected thereto, thereby constituting a large-capacity magnetic disk unit.

Now, the effect of the embodiments according to the present invention is specifically described below in comparison with comparative examples that depart from the scope of the claims. First, for comparison purposes, the head having the structure of Figs. 1 and 2 described in the section of the prior

art was prepared. After the deposition of the films, heat treatment was performed for five hours at a temperature of 250°C while a magnetic field of  $7.9 \times 10^5 \text{ A/m}$  was being applied in the direction perpendicular to the magnetic field applied upon deposition.

The following materials were employed as each component that forms the head. The composition of each of the material shown below is that of the targets employed for sputtering (atom %), and the numerals in the parentheses denote the thickness of the layer.

Substrate: alumina of  $3 \mu\text{m}$  layered on an altic layer 1.2mm in thickness

Lower shield layer:  $\text{Co}_{89}\text{Zr}_4\text{Ta}_4\text{Cr}_3$  ( $1 \mu\text{m}$ )

Lower conductive layer: Ta ( $20 \mu\text{m}$ )

Upper electrode layer: not available

Upper shield layer:  $\text{Co}_{65}\text{Ni}_{12}\text{Fe}_{23}$  ( $1 \mu\text{m}$ )

Insulation layer: alumina (20nm)

Underlying layer vertical bias: Cr (10nm)

Vertical bias:  $\text{Co}_{74.5}\text{Cr}_{10.5}\text{Pt}_{15}$  (33nm)

Lower gap layer: not available

Upper gap layer: not available

Upper layer: Ta (5nm)

Underlying layer for free layer: Ta (3nm)

Fixing layer:  $\text{Pt}_{46}\text{Mn}_{54}$  (20nm)

Fixed layer: three-layer film ( $\text{Co}_{90}\text{Fe}_{10}$  (3nm) /Ru (0.7nm) / $\text{Co}_{50}\text{Fe}_{50}$  (3nm))

Non-magnetic layer: Al oxide (0.7nm)

Free layer:  $\text{Ni}_{82}\text{Fe}_{18}$  (5nm)

Upper layer: Ta (3nm)

This head was machined and sliced into a merged read/write head like the read head 45 shown in Fig. 105 and then data was written onto and read from a CoCrTa-based medium. And, the write track was  $0.7\mu\text{m}$  in width and the read track was  $0.4\mu\text{m}$  in width.

The TMR element portion was fabricated through the photoresist process employing the i-line and the milling process. Upon preparing the coil portion of the write head, the photoresist was held at a temperature of  $250^{\circ}\text{C}$  for two hours and thereby hardened.

This process caused the fixed layer and the fixing layer to rotate their orientation of magnetization which should be directed along the height of the element, thereby resulting in improper operation of the magneto-resistance effect element. Accordingly, after the read head portion and the write head portion were prepared, magnetization heat treatment was performed for one hour at a temperature  $200^{\circ}\text{C}$  in a magnetic field of  $4.0 \times 10^4 \text{A/m}$ . Almost no rotation of the magnetization easy axis of the free layer in the orientation of magnetization caused by this magnetization heat treatment was observed in the magnetization curve.

It was assumed that the coercive force of the medium was  $2.4 \times 10^5 \text{A/m}$ , and  $\text{MrT}$  (the product of residual magnetization and film thickness) was  $0.35 \text{emu/cm}^2$ . Using ten prototype heads of each structure, the read output, S/N ratio, and effective track width were measured. The results of measurement made on the structure of Fig. 2 are shown in Table 1, and the results of measurement made on the structure of Fig. 1 are shown in Table 2.

Table 1

Element No.	Output (mV)	(S/N) ratio (dB)
1	3.1	21
2	3.0	20
3	2.8	19
4	2.9	18
5	2.9	19
6	3.1	21
7	2.9	19
8	3.1	19
9	3.0	21
10	2.8	19

Table 2

Element No.	Output (mV)	(S/N) ratio (dB)
1	1.2	17
2	1.1	16
3	0	0
4	0.5	12
5	0.2	5
6	0.3	8
7	0.4	9
8	0.2	2
9	0	0
10	0.3	8

The structure of Fig. 1 provides a read output as high as 2.8 to 3.1mV but S/N ratio as low as 18 to 21dB. This was caused by Barkhausen noise included in the read signal. It was found by

measuring the R-H loop of the head that the hysteresis produced by the inversion of the free layer magnetization was so high as to cause the Barkhausen noise involved in the magnetic wall displacement of the free layer. In the structure of Fig. 1, it is considered that since the vertical bias layer and the free layer are isolated by the insulation layer, the vertical bias magnetic field is not applied sufficiently to the free layer, so that the vertical bias magnetic field does not contribute to the reduction in Barkhausen noise.

On the other hand, in the structure of Fig. 2, the read output was as low as 0 to 1.2mV, and accordingly the (S/N) ratio was as low as 0 to 17dB. This is because the sense current leaks out to the vertical bias layer 2b and thus does not conduct through the non-magnetic layer 4. In this structure, it may be possible in principle to prevent the leakage of the sense current to the vertical bias layer 2b; however, the leakage cannot be prevented. This is conceivably because the structure cannot be precisely fabricated to prevent the leakage of the sense current to the vertical bias layer 2b and conduct the sense current sufficiently through the non-magnetic layer 4. This results from the fact that the vertical bias layer 2b is in close proximity to the end portion of the non-magnetic layer 4 (barrier layer) in the layered body made up of the fixed layer 5, the non-magnetic layer 4, and the free layer 3.

Then, as an embodiment of the present invention, fabricated was the magneto-resistance effect head of the structure shown in Figs. 10, 21, 31, 37, 49, and 64. And, the following materials were employed as each component that forms

the magneto-resistance effect head.

Substrate: alumina of  $3\mu\text{m}$  layered on an altic layer 1.2mm in thickness

Lower shield layer:  $\text{Co}_{89}\text{Zr}_4\text{Ta}_4\text{Cr}_3$  ( $1\mu\text{m}$ )

5 Lower conductive layer: Ta ( $20\mu\text{m}$ )

Upper electrode layer: not available

Upper shield layer:  $\text{Co}_{65}\text{Ni}_{12}\text{Fe}_{23}$  ( $1\mu\text{m}$ )

Insulation layer: alumina (20nm)

Underlying layer for vertical bias layer: Cr (10nm)

10 Vertical bias:  $\text{Co}_{74.5}\text{Cr}_{10.5}\text{Pt}_{15}$  (33nm)

Lower gap layer: not available

Upper gap layer: not available

Upper layer: Ta (5nm)

Underlying layer for free layer: Ta (3nm)

15 Underlying layer for magnetic layer: Ta (3nm)

Fixing layer:  $\text{Pt}_{46}\text{Mn}_{54}$  (20nm)

Second fixing layer:  $\text{Pt}_{46}\text{Mn}_{54}$  (20nm)

Fixed layer: three-layer film ( $\text{Co}_{90}\text{Fe}_{10}$  (3nm) /Ru (0.7nm) / $\text{Co}_{50}\text{Fe}_{50}$  (3nm))

20 Second fixed layer: three-layer film ( $\text{Co}_{90}\text{Fe}_{10}$  (3nm) /Ru (0.7nm) / $\text{Co}_{50}\text{Fe}_{50}$  (3nm))

First non-magnetic layer: Al oxide (0.7nm)

Second non-magnetic layer: Ru (0.75nm)

Third non-magnetic layer: Ru (0.75nm)

25 Fourth non-magnetic layer: Ru (0.75nm)

Fifth non-magnetic layer: Al oxide (0.7nm)

Free layer:  $\text{Ni}_{82}\text{Fe}_{18}$  (5nm)

Magnetic layer:  $\text{Ni}_{82}\text{Fe}_{18}$  (5nm)

Upper layer: Ta (3nm)

This head was machined and sliced into a merged read/write head like the read head 45 shown in Fig. 105 and then data was written onto and read from a CoCrTa-based medium. And, the write track was  $0.7\mu\text{m}$  in width and the read track was  $0.4\mu\text{m}$  in width.

The TMR element portion was fabricated through the photoresist process employing the i-line and the milling process. Upon preparing the coil portion of the write head, the photoresist was held at a temperature of  $250^{\circ}\text{C}$  for two hours and thereby hardened.

This process caused the fixed layer and the fixing layer to rotate their orientation of magnetization, which should be directed along the height of the element, thereby resulting in improper operation of the magneto-resistance effect element. Accordingly, after the read head portion and the write head portion were prepared, magnetization heat treatment was performed for one hour at a temperature  $200^{\circ}\text{C}$  in a magnetic field of  $4.0 \times 10^4 \text{A/m}$ . Almost no rotation of the magnetization easy axis of the free layer in the orientation of magnetization caused by this magnetization heat treatment was observed in the magnetization curve.

It was assumed that the coercive force of the medium was  $2.4 \times 10^5 \text{A/m}$ , and  $M_r T$  (the product of residual magnetization and film thickness) was  $0.35 \text{emu/cm}^2$ . Using ten prototype heads of each structure, the read output, S/N ratio, and effective track width were measured. The results of measurement made on the structure of Figs. 10, 21, 31, 37, 49, and 64 are shown in Tables 1 to 8.

Table 3

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu\text{m}$ )
1	3.0	27	0.61
2	3.1	26	0.59
3	2.9	27	0.60
4	3.0	28	0.61
5	2.8	26	0.57
6	3.0	27	0.57
7	3.1	28	0.60
8	3.0	27	0.59
9	2.8	26	0.58
10	2.8	25	0.57

Table 4

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu\text{m}$ )
1	3.0	27	0.58
2	2.8	28	0.59
3	2.9	27	0.57
4	2.8	27	0.57
5	2.7	26	0.59
6	3.0	25	0.60
7	3.1	27	0.59
8	3.0	28	0.58
9	3.1	26	0.57
10	3.0	25	0.60



Table 5

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu\text{m}$ )
1	3.2	27	0.58
2	3.1	27	0.57
3	2.9	28	0.56
4	2.7	26	0.58
5	2.8	27	0.60
6	2.9	27	0.60
7	2.8	26	0.58
8	3.0	27	0.57
9	3.0	28	0.59
10	3.1	27	0.60

Table 6

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu\text{m}$ )
1	2.9	28	0.58
2	2.8	27	0.59
3	2.7	26	0.56
4	2.8	27	0.58
5	2.9	27	0.56
6	2.9	26	0.55
7	2.7	27	0.54
8	2.8	26	0.58
9	2.7	26	0.56
10	2.9	28	0.57

Table 7

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu$ m)
1	2.8	27	0.55
2	2.7	28	0.54
3	2.8	26	0.53
4	2.9	27	0.54
5	2.9	28	0.54
6	3.0	27	0.542
7	2.8	26	0.53
8	2.9	27	0.54
9	2.9	28	0.55
10	2.8	25	0.51

Table 8

Element No.	Output (mV)	(S/N) ratio (dB)	Effective track width ( $\mu$ m)
1	2.9	25	4.8
2	2.9	26	4.9
3	2.7	26	4.8
4	2.6	27	5.1
5	2.7	26	4.8
6	2.8	26	5.0
7	2.5	25	5.1
8	2.5	27	4.9
9	2.6	25	4.6
10	2.6	25	4.5

It can be seen that any one of the structures shown in Figs. 10, 21, 31, 37, 49 and 64 provides a S/N ratio of 25dB or

more, thus providing a significantly improved S/N ratio in comparison with the prior-art example. This is because any one of the structures can prevent the sense current from bypassing the barrier layer, and therefore provide sufficient output and  
5 successfully apply a proper amount of vertical bias magnetic field to the free layer, thereby making it possible to sufficiently reduce noise and thus provide a good S/N ratio. Among the magneto-resistance effect heads shown in Figs. 10, 21, 31, 37, 49, and 64, the one shown in Fig. 64 has the smallest  
10 effective track width and provides the best result. This is conceivably because the magneto-resistance effect head shown in Fig. 64 has a layered anti-ferromagnetic layer structure of the magnetic layer 8, the third non-magnetic layer 13, and the second magnetic layer 12. This structure is thereby prevented from  
15 being subjected to the effect of the leakage magnetic field from the medium, so that the read effective track width is determined only by the width of the free layer 3b.